



Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00010	2	Absperrschieber mit Handrad Gate valve with handwheel	10"	Cl. 600 BW 273,0 x 4,19	ASTM A 494 CW-6MC	Valve Ident - No.: "S 555" LPI 3210-1LP Geeignet für den Sauerstoffeinsatz Suitable for oxygen service

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 158 bar Wasser / water (120 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 115 bar Wasser / water (120 sec)*
Rückdichtung / backseat = 115 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (120 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
--------------	------------

Sachbearbeiter W Glass

W Glass

W Glass

Lurqi OGC PO,- No.: 4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

Zeugnis-Nr.

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: 28334
		DATE: 14/12/04
		SHEET:

Cliente/Cliet.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 6
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1230 °C	MODO DE FUSION: INDUCTION FURNACE TYPE OF MELTING:
--------------------------------	------------------	--

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	10" – 600 Lbs	Heat No.:	W341
	Gate Bonnet	10" – 600 Lbs	Heat No.:	W341
	Gate Wedge	10" – 600 Lbs	Heat No.:	W341

CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 494 CW-6MC	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-------------------	---	------------------


ANÁLISIS QUÍMICO – CHEMICAL ANALYSIS												Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	Fe			
Solicitado Requirements (max)	0.06	1.00	1.00	0.015	0.015	20.0- 23.0	Balan.	8.0- 10.0	3.15- 4.50	5.0			
W341	0.054	0.700	0.474	0.001	0.003	22.026	59.950	8.110	3.210	4.600		6	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										Resiliencia Impact Test (ISO V Prob) J; T 20°C		
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB					
Solicitado Requirements	Lo = 4D	12.5	485	275	25		232					
W341	Lo = 4D	12.5	506	293	39		157					

Insp. Visual y C. Dimensional Visual Insp. And Dimens check	Ensayo Magnaflux Magnaflux test	Insp. Por Gammagrafia Gamma-graphic Inspection	Ensayo de Presión Pressure Test	Insp. Por Ultrasonidos Ultrasonic Test
S/ MSS-SP-55	Satisfactory			

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, has been tested and complies to the material requirements of the purchase order. The results above indicated exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.







SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No. 3210-1LP

Work Order	3210-12/04	Item:	
Customer	VALVES ENTERPRISE	P. O. No.:	P-200450
Valve Type:	GATE 10" - 600#	Valve Tag:	S555
Serial No			
Drawing:	1.600BW	Surface Conditions:	MACHINED
Part:	100 % BW-ENDS	Material:	A 494 CW-6MC

Reference Procedure:	E 165	
Acceptance Standards:	ANSI B 16.34 Anex. D	
Precleaned by	WATER	
Type of penetrant:	ARDROX 906P	
Rinsed by	WATER	
Type of developer	ARDROX 9D1B	
Penetr. Time (min.):	17' TO 23'	Developer Time (min.): 19' TO 25'
Temperature (°C):	18 °C	

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Nonlinear indications	☐	☒	☒	☐

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by Fernando
Level II Acc. to SNT-TC-1A

Approved by Fernando
Level II Acc. to SNT-TC-1A

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER
Sign.

Sign.

Sign.

Date: 11/01/05

15 ENE 2005
Date: 15/01/05

Date

Date

QA/QC Department



Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job – No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00020	2	Absperrschieber mit Handrad Gate valve with handwheel	2"	Cl.150 RF	ASTM A 351 CF8C	Valve Ident – No.: " S 655 " LPI 20-S655-W5836 20-S655-W5837 RE W5873

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 30 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 22 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 22 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	<i>W. Glass</i>

Lurgi Job - No.: 69690-10
Luraji OGC PO.- No.: 4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5836-W5837
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 6
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	2" – 150 Lbs	Heat No.:	Y952
	Gate Bonnet	2" – 150 Lbs	Heat No.:	Y952
	Gate Wedge	2" – 150 Lbs	Heat No.:	Y952

CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO – CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
Y952	0.053	0.86	1.32	0.019	0.022	18.35	9.42	0.024	0.53		6	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm ²	L. Elástico Yield Point N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
Y952	Lo = 4D	12.5	535	264	41	68	192	68	69	72
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gamma-graphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, has been tested and complies to the material requirements of the purchase order. The results above indicated are a true and correct transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.

Quality

Control Department

SPECIALTY VALVES RESEARCH, S.A.

VALVES MANUFACTURER

14 ENE. 2005

QA/QC Departament





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **20-S655-W5836**

Work Order: **W5836-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 150Lb 2"**

Heat No.: **Y952**

Drawing: **1. 150Lb RF**

Part: **Flange end**

Item: **20**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5836**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by **Level II SNT-TC-1A**
EN 473 17 FEB 2005 **EN 473**

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **20-S655-W5837**

Work Order: **W5837-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 150Lb 2"**

Heat No.: **Y952**

Drawing: **1. 150Lb RF**

Part: **Flange end**

Item: **20**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5837**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by: **SPECIALTY VALVES RESEARCH**
Level II SNT-TC-1A
EN 473

Approved by: **SPECIALTY VALVES RESEARCH**
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5876
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 1500LB 2"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48023	


X Rays KV : 7 RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400, 360x50/360x80	IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20	Material Thickness: 30		
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 3 MIN	

Evaluation standard for steel castings radiographic examination (See Back)		Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form		ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1		II	/	/	/	/	/	/	I	OK
R2	2		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5		II	/	/	/	/	/	/	I	OK
R6	6		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48023
Contract:	HH-02536	Part No.	W5876
Drawing:	1500LB 2"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shield
R1 - R8	KODAK AA400	30	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00030	4	Absperrschieber mit Handrad Gate valve with handwheel	2"	Cl.300 RF	ASTM A 351 CF8C	Valve Ident - No.: "S 655" LPI 30-S655-W5838 30-S655-W5839 30-S655-W5840 30-S655-W5841

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 75 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 55 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 55 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION GmbH & Co. KG**

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



W. Glass
W. Glass

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	N°/Nr.: W5838-W5839- W5840-W5841
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido N° Purchase Order: HH-02536	Cantidad: Quantity: 12
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

C. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--------------------------------	------------------	--

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	2" – 300 Lbs	Heat No.:	6952
	Gate Bonnet	2" – 300 Lbs	Heat No.:	6952
	Gate Wedge	2" – 300 Lbs	Heat No.:	6952


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO – CHEMICAL ANALYSIS												N° de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V			
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00				
6952	0.062	0.79	1.25	0.024	0.026	18.54	9.44	0.018	0.62			12	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm ²	L. Elástico Yield Point N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
6952	Lo = 4D	12.5	500	242	39	62	196	65	67	66
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gamma-graphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

Hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 30-S655-W5838

Work Order: W5838-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 300Lb 2"

Heat No.: 6952

Drawing: 1. 300Lb RF

Part: Flange end

Item: 30

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5838

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A

EN 473

Approved by

Level II SNT-TC-1A

EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 30-S655-W5839

Work Order: W5839-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 300Lb 2"

Heat No.: 6952

Drawing: 1. 300Lb RF

Part: Flange end

Item: 30

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5839

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 ENE. 2005
Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department
Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **30-S655-W5840**

Work Order: **W5840-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 300Lb 2"**

Heat No.: **6952**

Drawing: **1. 300Lb RF**

Part: **Flange end**

Item: **30**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5840**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A

EN 473

Approved by

Level II SNT-TC-1A

EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17

ENE 2005

Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC

Department

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **30-S655-W5841**

Work Order: **W5841-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 300Lb 2"**

Heat No.: **6952**

Drawing: **1. 300Lb RF**

Part: **Flange end**

Item: **30**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5841**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00040	25	Absperrschieber mit Handrad Gate valve with handwheel	2"	Cl.600 RF	ASTM A 351 CF8C	Valve Ident - No.: "S 655" LPI 40-S655-W5842 to 40-S655-W5866

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 150 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 110 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 110 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)


Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Gasse*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5842 to W5866
		DATE: 14/12/04
		SHEET:

Cliente/Cliet.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 75
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

H.T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
----------------------------------	------------------	--

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	2" – 600 Lbs	Heat No.:	6952
	Gate Bonnet	2" – 600 Lbs	Heat No.:	6952
	Gate Wedge	2" – 600 Lbs	Heat No.:	6952


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO – CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
6952	0.062	0.79	1.25	0.024	0.026	18.54	9.44	0.018	0.62		75	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm ²	L. Elástico Yield Point N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
6952	Lo = 4D	12.5	500	242	39	62	196	65	67	66
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

we hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5842**

Work Order: **W5842-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5842**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Approved by

Level II SNT-TC-1A

Level II SNT-TC-1A

EN 473

EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 ENE 2005
Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department
Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5843

Work Order: **W5843-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5843

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

7 ENE. 2005
Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department
Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5844

Work Order: W5844-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 600Lb 2"

Heat No.: 6952

Drawing: 1. 600Lb RF

Part: Flange end

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5844

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473
17 ENE. 2005

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5845**

Work Order: **W5845-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5845**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department
Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5846

Work Order: **W5846-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5846

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A
EN 473

Approved by

Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5847

Work Order: **W5847-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5847

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5848**

Work Order: **W5848-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5848**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5849**

Work Order: **W5849-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5849**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A

EN 473

Approved by

Level II SNT-TC-1A

EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5850

Work Order: **W5850-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5850

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 JAN 2005
Sign.

Sign.

Sign.

Date January 17, 2005 QA/

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5851

Work Order: **W5851-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5851

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 JNE 2005
Sign.

Sign.

Sign.

Date January 17, 2005

QC Department
Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5852

Work Order: W5852-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 600Lb 2"

Heat No.: 6952

Drawing: 1. 600Lb RF

Part: Flange end

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5852

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17.ENE. 2005
Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department
Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5853**

Work Order: **W5853-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5853**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5854**

Work Order: **W5854-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5854

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 Jan 2005

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5855**

Work Order: **W5855-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5855**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5856**

Work Order: **W5856-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5856

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A

EN 473

Approved by

Level II SNT-TC-1A

EN 473

WITNESS POINT CUSTOMER

☐ YES

☐ NOT

☐ OTHERS

Sign.

17 JUNE 2005

Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5857**

Work Order: **W5857-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5857**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

**Level II SNT-TC-1A
EN 473**

Approved by

**Level II SNT-TC-1A
EN 473**

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17

ENE. 2005
Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5858**

Work Order: **W5858-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5858**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A

EN 473

Approved by

Level II SNT-TC-1A

EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 ENE 2005

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5859**

Work Order: **W5859-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5859**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5860**

Work Order: **W5860-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5860

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17

ENE 2005
Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department
Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5861**

Work Order: **W5861-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5861**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5862

Work Order: **W5862-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5862**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

**Level II SNT-TC-1A
EN 473**

Approved by

**Level II SNT-TC-1A
EN 473**

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5863

Work Order: W5863-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 600Lb 2"

Heat No.: 6952

Drawing: 1. 600Lb RF

Part: Flange end

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5863

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

QA/QC Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **40-S655-W5864**

Work Order: **W5864-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5864

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5865

Work Order: W5865-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 600Lb 2"

Heat No.: 6952

Drawing: 1. 600Lb RF

Part: Flange end

Item: 40

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5865

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Approved by

WITNESS POINT CUSTOMER

Level II SNT-TC-1A
EN 473 VALVE MANUFACTURER EN 473

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

QA/QC Department

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 40-S655-W5866

Work Order: **W5866-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **40**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5866**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00050	2	Absperrschieber mit Handrad Gate valve with handwheel	4"	Cl.300 RF	ASTM A 351 CF8C	Valve Ident - No.: "S 655" LPI 50-S655-W5867 50-S655-W5868

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 75 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 55 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 55 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION GmbH & Co. KG**

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*

28.02.2005



CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To

Nº/Nr.: W5867-W5868

DATE: 14/12/04

SHEET:

Cliente/Client.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: HH-02536

Cantidad:

Quantity: 6

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

T. CONDICION
CONDITION T.T.

SOLUTION 1050 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

Gate Body

4" - 300 Lbs

Heat No.:

6952

Gate Bonnet

4" - 300 Lbs

Heat No.:

6952

Gate Wedge

4" - 300 Lbs

Heat No.:

6952

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 351 CF8C

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS

COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V	Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
6952	0.062	0.79	1.25	0.024	0.026	18.54	9.44	0.018	0.62		6	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
6952	Lo = 4D	12.5	500	242	39	62	196	65	67	66
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are the exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are filed in our factory, emitted by our homologated suppliers.

Quality Control Department

SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

14 ENE. 2005

QA/QC Department



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 50-S655-W5867

Work Order: **W5867-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 300Lb 4"**

Heat No.: **6952**

Drawing: **1. 300Lb RF**

Part: **Flange end**

Item: **50**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5867**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by: **SPECIALTY VALVES RESEARCH**
Level II SNT-TC-1A
EN 473 17 ENE 2005 EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign. **QA/OC** Signament

Sign.

Sign.

Date **January 17, 2005**

Date **January 17, 2005**

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 50-S655-W5868

Work Order: **W5868-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 300Lb 4"**

Heat No.: **6952**

Drawing: **1. 300Lb RF**

Part: **Flange end**

Item: 50

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5868

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A
EN 473

Approved by

Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00060	3	Absperrschieber mit Handrad Gate valve with handwheel	8"	Cl.600 RF	ASTM A 351 CF8C	Valve Ident - No.: "S 655" LPI 60-S655-W5869 60-S655-W5870 60-S655-W5871

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 150 bar Wasser / water (120 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 110 bar Wasser / water (120 sec)*
Rückdichtung / backseat = 110 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (120 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION GmbH & Co. KG**

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
--------------	------------

Seite / Page 1

Sachbearbeiter

W. Glass

W. Glass

W. Glass

**Kommissions-Nr. /
Reference No.**

Lurgji Job - No.: 69690-10

Lurgi OGC PO, - No.: 4567571 - 000 / 1.69690 / 136

HH-02536

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5869
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 3
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

C. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--------------------------------	------------------	--

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	8" – 600 Lbs	Heat No.:	K48013
	Gate Bonnet	8" – 600 Lbs	Heat No.:	Y952
	Gate Wedge	8" – 600 Lbs	Heat No.:	6952


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO – CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48013	0.053	0.82	1.22	0.020	0.021	18.40	9.34	0.016	0.53		1	
Y952	0.053	0.86	1.32	0.019	0.022	18.35	9.42	0.024	0.53		1	
6952	0.062	0.79	1.25	0.024	0.026	18.54	9.44	0.018	0.62		1	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48013	Lo = 4D	12.5	495	268	40	62	201	66	68	69
Y952	Lo = 4D	12.5	535	264	41	68	192	68	69	72
6952	Lo = 4D	12.5	500	242	39	62	196	65	67	66
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gamma-graphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

we hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.



**CERTIFICADO DE MATERIALES s/
MILL CERTIFICATE Acc. To**

Nº/Nr.: W5870-W5871

DATE: 14/12/04

SHEET:

Cliente/Client.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: **HH-02536**

Cantidad:

Quantity: **6**

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

T. CONDICION
CONDITION T.T.

SOLUTION 1050 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

Gate Body

8" -600 Lbs

Heat No.:

K48012

Gate Bonnet

8" - 600 Lbs

Heat No.:

Y952

Gate Wedge

8" - 600 Lbs

Heat No.:

6952

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 351 CF8C

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS

COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V	Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48012	0.06	0.69	1.16	0.021	0.023	18.44	9.33	0.017	0.62		2	
Y952	0.053	0.86	1.32	0.019	0.022	18.35	9.42	0.024	0.53		2	
6952	0.062	0.79	1.25	0.024	0.026	18.54	9.44	0.018	0.62		2	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm ²	L. Elástico Yield Point N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48012	Lo = 4D	12.5	505	261	38	62	188	62	72	69
Y952	Lo = 4D	12.5	535	264	41	68	192	68	69	72
6952	Lo = 4D	12.5	500	242	39	62	196	65	67	66
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gamma-graphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

I hereby certify that the material described above, has been tested and complies the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.

Quality Control Department

14 ENE. 2005

QA/QC Departament



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **60-S655-W5869**

Work Order: **W5869-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 8"**

Heat No.: **K48013**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **60**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5869**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by **Level II SNT-TC-1A**
EN 473 17 ENE 2005

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 60-S655-W5870

Work Order: **W5870-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 8"**

Heat No.: **K48012**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: 60

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5870

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 60-S655-W5871

Work Order: **W5871-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 8"**

Heat No.: **K48012**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **60**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5871**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by **Level II SNT-TC-1A**
EN 473 SPECIALTY VALVES RESEARCH, VALVES MANUFACTURER

Approved by **Level II SNT-TC-1A**
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 ENR 2005

Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department

Date January 17, 2005

Date

Date



Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00070	4	Absperrschieber mit Handrad Gate valve with handwheel	10"	Cl.600 RF	ASTM A 351 CF8C	Valve Ident - No.: "S 655" LPI 70-S655-W5872 70-S655-W5873 70-S655-W5874 70-S655-W5875

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 150 bar Wasser / water (120 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 110 bar Wasser / water (120 sec)*
Rückdichtung / backseat = 110 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (120 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION GmbH & Co. KG**

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Materialdokumentations - Deckblatt

Material Cover Sheet

Datum / Date	25.02.2005
--------------	------------

Seite / Page 1

Sachbearbeiter
Person in charge

W. Glass
Wally

**Kommissions-Nr. /
Reference No.**

Lurgi Job - No.: 69690-10
Lurgi OGC PO,- No.: 4567571 - 000 / 1.69690 / 136

HH-02536

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

28.02.2005

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5872-W5874
		DATE: 14/12/04
		SHEET:

Cliente/Cient.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 6
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp:	
		

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--------------------------------	------------------	--

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	10" – 600 Lbs	Heat No.:	K48011
	Gate Bonnet	10" – 600 Lbs	Heat No.:	Y952
	Gate Wedge	10" – 600 Lbs	Heat No.:	K48011


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO – CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48011	0.065	0.71	1.34	0.022	0.017	18.47	9.35	0.017	0.58		4	
Y952	0.053	0.86	1.32	0.019	0.022	18.35	9.42	0.024	0.53		2	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48011	Lo = 4D	12.5	501	255	38	68	195	68	69	75
Y952	Lo = 4D	12.5	535	264	41	68	192	68	69	72
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

I hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.



**CERTIFICADO DE MATERIALES s/
MILL CERTIFICATE Acc. To**

Nº/Nr.: W5873-W5875

DATE: 14/12/04

SHEET:

Cliente/Client.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: **HH-02536**

Cantidad:

Quantity: 6

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

T. CONDICION
CONDITION T.T.

SOLUTION 1050 °C

MODULO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

Gate Body

10" -600 Lbs

Heat No.:

K48012

Gate Bonnet

10" - 600 Lbs

Heat No.:

Y952

Gate Wedge

10" - 600 Lbs

Heat No.:

K48012

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 351 CF8C

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS

COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V	Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48012	0.06	0.69	1.16	0.021	0.023	18.44	9.33	0.017	0.62		4	
Y952	0.053	0.86	1.32	0.019	0.022	18.35	9.42	0.024	0.53		2	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48012	Lo = 4D	12.5	505	261	38	62	188	62	72	69
Y952	Lo = 4D	12.5	535	264	41	68	192	68	69	72
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

hereby certify that the material described above, has been tested and complies the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.

Quality

SPECIALTY VALVES RESEARCH, S.A.
Control Department

14 ENE. 2005

QA/QC Department



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 70-S655-W5872

Work Order: W5872-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 600Lb 10"

Heat No.: K48011

Drawing: 1. 600Lb RF

Part: Flange end

Item: 70

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5872

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 70-S655-W5874

Work Order: **W5874-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 10"**

Heat No.: **K48011**

Drawing: **1. 600Lb RF**

Part: **Flange end**

Item: **70**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5874**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473
17 ENE. 2005

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

QA/QC Department
Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **70-S655-W5873**

Work Order: W5873-06/12
Customer: KLAUS UNION
Valve Type: Gate Valve 600Lb 10"
Heat No.: K48012
Drawing: 1. 600Lb RF
Part: Flange end

Item: 70
P. O. No.: HH-02536
Quantity: 1
Serials No.: W5873
Surface Conditions: AS RAW
Material: ASTM A351 CF8C

Reference Procedure: E165
Acceptance Standards: ANSI B 16.34
Precleaned by: WATER
Type of penetrant: HP-ST
Rinsed by: HD-ST
Type of developer: HR-ST
Penetr. Time (min.): 5-20
Temperature (°C): 15°C

Developer Time (min.): 7-30

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473
17 JAN 2005

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **70-S655-W5875**

Work Order: **W5875-06/12**
Customer: **KLAUS UNION**
Valve Type: **Gate Valve 600Lb 10"**
Heat No.: **K48012**
Drawing: **1. 600Lb RF**
Part: **Flange end**

Item: **70**
P. O. No.: **HH-02536**
Quantity: **1**
Serials No.: **W5875**
Surface Conditions: **AS RAW**
Material: **ASTM A351 CF8C**

Reference Procedure: **E165**
Acceptance Standards: **ANSI B 16.34**
Precleaned by: **WATER**
Type of penetrant: **HP-ST**
Rinsed by: **HD-ST**
Type of developer: **HR-ST**
Penetr. Time (min.): **5-20**
Temperature (°C): **15°C**

Developer Time (min.): **7-30**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473
17 ENE 2005

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00080	2	Absperrschieber mit Handrad Gate valve with handwheel	2"	Cl.1500 BW 60,3 x 5,54	ASTM A 351 CF8C	Valve Ident - No.: "S 656" LPI 80-S656-W5876 80-S656-W5877 RE-Report: W5876, W5877

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 375 bar Wasser / water (600 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 275 bar Wasser / water (600 sec)*
Rückdichtung / backseat = 275 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION GmbH & Co. KG**

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	<i>W. Glass</i>

Seite / Page 1

Sachbearbeiter

W. Glass

W. Glass

W. Glass

69690-10
4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

Pos.	Benennung	Spezifikation	Stück	Bauteil	Ident.-Nr.	Werkstoff	Hersteller	Chargen-Nr.	Probe	Zeugnis-Nr.
Item	Designation	Valve Ident - No.:	Pc.	Piece parts	Ident.-No.	Material	Manufacturer	Heat No.	Sample No.	Cert. No.

**CERTIFICADO DE MATERIALES s/
MILL CERTIFICATE Acc. To**

Nº/Nr.: W5876-W5877

DATE: 14/12/04

SHEET:

Cliente/Client.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: **HH-02536**

Cantidad:

Quantity: **6**

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

T. CONDICION
CONDITION T.T.

SOLUTION 1050 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

Gate Body

2" -1500 Lbs

Heat No.:

K48023

Gate Bonnet

2" -1500 Lbs

Heat No.:

6952

Gate Wedge

2" -1500 Lbs

Heat No.:

K48023

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 351 CF8C

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS


COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00				
K48023	0.058	0.66	1.24	0.025	0.026	18.56	9.47	0.018	0.69			4	
6952	0.062	0.79	1.25	0.024	0.026	18.54	9.44	0.018	0.62			2	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48023	Lo = 4D	12.5	500	258	39	69	198	67	69	77
6952	Lo = 4D	12.5	500	242	39	62	196	65	67	66
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

hereby certify that the material described above, has been tested and complies the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **80-S656-W5876**

Work Order: **W5876-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 1500Lb 2"**

Heat No.: **K48023**

Drawing: **1. 1500Lb BW**

Part: **BW end**

Item: **80**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5876**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473
17 ENE. 2005

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 80-S656-W5877

Work Order: **W5877-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 1500Lb 2"**

Heat No.: **K48023**

Drawing: **1. 1500Lb BW**

Part: **BW end**

Item: **80**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5877**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5877
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 1500LB 2"	Radiographed at: Shop: ☒ ☐
Material : CF8C Heat Number: K48023	Field: ☐

X Rays KV : 7 RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80	IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20	Material Thickness: 30		
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 3 MIN	

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1		II	/	/	/	/	/	/	I	OK
R2	2		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5		II	/	/	/	/	/	/	I	OK
R6	6		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados. We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.	 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER 14 ENE. 2005 QA/QC Departament
--	--


 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48023
Contract:	HH-02536	Part No.	W5877
Drawing:	150OLB 2"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1 - R6	KODAK AA400	30	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5876
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 1500LB 2"	Radiographed at: Shop: ☒ ☐
Material : CF8C Heat Number: K48023	Field: ☐

X Rays KV : 7 RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400, 360x50/360x80	IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20	Material Thickness: 30		
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 3 MIN	

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1		II	/	/	/	/	/	/	I	OK
R2	2		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5		II	/	/	/	/	/	/	I	OK
R6	6		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.


SPECIALTY VALVES RESEARCH, S.A.
 VALVES MANUFACTURER

 14 ENE. 2005

 QA/QC Department


 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48023
Contract:	HH-02536	Part No:	W5876
Drawing:	1500LB 2"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shield
R1 - R8	KODAK AA400	30	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00090	3	Absperrschieber mit Handrad Gate valve with handwheel	2"	Cl.1500 BW 60,3 x 8,74	ASTM A 351 CF8C	Valve Ident - No.: "S 656" LPI 90-S656-W5878 to W5880 RE W5878 to W5880

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 375 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 275 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 275 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: Walter Glass

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Materialdokumentations - Deckblatt

Material Cover Sheet

Datum / Date	25.02.2005
--------------	------------

Seite / Page 1

Sachbearbeiter
Person in charge

W. Glass

W. Glass
Ralf JB

**Kommissions-Nr. /
Reference No.**

Lurgi Job - No.: 69690-10
Lurgi OGC PO₁ - No.: 4567571 - 000 / 1.69690 / 136

HH-02536

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5878-W5879-W5880
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 6
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--------------------------------	------------------	--

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	2" -1500 Lbs	Heat No.:	K48023
	Gate Bonnet	2" -1500 Lbs	Heat No.:	6952
	Gate Wedge	2" -1500 Lbs	Heat No.:	K48023


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48023	0.058	0.66	1.24	0.025	0.026	18.56	9.47	0.018	0.69		4	
6952	0.062	0.79	1.25	0.024	0.026	18.54	9.44	0.018	0.62		2	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm ²	L. Elástico Yield Point N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48023	Lo = 4D	12.5	500	258	39	69	198	67	69	77
6952	Lo = 4D	12.5	500	242	39	62	196	65	67	66
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aqui ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

I hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **90-S656-W5878**

Work Order: **W5878-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 1500Lb 2"**

Heat No.: **K48023**

Drawing: **1. 1500Lb BW**

Part: **BW end**

Item: 90

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5878

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 90-S656-W5879

Work Order: W5879-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 1500Lb 2"

Heat No.: K48023

Drawing: 1. 1500Lb BW

Part: BW end

Item: 90

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5879

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 90-S656-W5880

Work Order: **W5880-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 1500Lb 2"**

Heat No.: **K48023**

Drawing: **1. 1500Lb BW**

Part: **BW end**

Item: 90

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5880

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.
QA/QC Department

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5878
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 1500LB 2"	Radiographed at: Shop: ☒ Field: ☐
Material : WC9 Heat Number: K48023	

X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80		IQT: ASTM 1B
Screens Type and Thickness :		Pb,0.05/0.20		Material Thickness: 30
Density : 1.5-4.0	Source Film Distance :	600MM		Exposure Time: 3 MIN

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1		II	/	/	/	/	/	/	I	OK
R2	2		II	A2	/	/	/	/	/	II	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5		II	/	B2	/	/	/	/	II	OK
R6	6		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.


SPECIALTY VALVES RESEARCH, S.A.
 VALVES MANUFACTURER

 14 ENE. 2005

 QA/QC Departament



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER


ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
PHONE:	+ (34) 94. 455. 51. 51
FAX:	+ (34) 94. 455. 51. 50
WEBB:	www.svrvalves.com
E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48023
Contract:	HH-02536	Part No.:	W5878
Drawing:	1500LB 2"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R6	KODAK AA400	30	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5879
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 1500LB 2"	Radiographed at: Shop: ☒ ☐
Material : CF8C Heat Number: K48023	Field: ☐


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80		IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20		Material Thickness: Thickness+2mm		
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 3 MIN		

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf	Accepted
R1	1		II	/	/	/	/	/	/	I	OK
R2	2		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5		II	/	/	/	/	/	/	I	OK
R6	6		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48023
Contract:	HH-02536	Part No:	W5879
Drawing:	1500LB 2"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shield
R1-R6	KODAK AA400	30	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5880
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE	Extension of Test: BW-ENDS
Drawing : 1500LB 10"	Radiographed at: Shop: ☒ ☐
Material : CF8C Heat Number: K48023	Field: ☐


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80		IQI: ASTM 1B
Screens Type and Thickness :		Pb,0.05/0.20		Material Thickness: 30
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time: 3MIN

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1		II	A1	/	/	/	/	/	I	OK
R2	2		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	B2	/	/	/	/	II	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5		II	/	/	/	/	/	/	I	OK
R6	6		II	/	B1	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48023
Contract:	HH-02536	Part No.	W5880
Drawing:	1500LB 10"	Descriptions:	GATE

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shield
R1-R6	KODAK AA400	30	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt
Customer:

Bestell-Nr.: Lurgi Job - No.: 69690-10
Order no.: Lurgi OGC PO.-No.: 4567571-000/1.69690/136

Project Name : 2nd Zagros Methanol Plant - Iran

Auftrag-Nr.: HH - 02536
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00100	9	Absperrschieber mit Handrad Gate valve with handwheel	3"	Cl.900 BW 88,9 x 5,49	ASTM A 351 CF8C	Valve Ident - No.: "S 656" LPI 100-S656-W5881 100-S656-W5882 to W5889 RE W5881 W5882 to 5889

Auslegung + Prüfung nach API 600 / API 598 / Nace MR 0175
Design and tests acc. to

Sicht- und Funktionsprüfung: o.k.
visual and functional test:

Festigkeits-/Dichtheitsprüfung: Festigkeit / shell test = 225 bar Wasser / water (60 sec)
strength-/tightness-test: Dichtheit Sitz / seat = 165 bar Wasser / water (60 sec)
Rückdichtung / backseat = 165 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: ohne Beanstandung !
result: no complaint !

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: Walter Glass

Anlage: Dokumentation gemäß Material-Dokumentationsdeckblatt
enclosure Documentation acc. to material cover sheet



Datum / Date	25.02.2005
--------------	------------

Datum / Date	25.02.2005
--------------	------------

Seite / Page 1

Sachbearbeiter	
Person in charge	

W. Glass

W. Glass
Walt's LPs

**Kommissions-Nr. /
Reference No.**

Lurgi Job - No.: **69690-10**

Lurqi OGC PO, - No.: 4567571 - 000 / 1.69690 / 136

HH-02536

Project Name:

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5881
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 3
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

H.T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	3" -900 Lbs	Heat No.:	K48025
	Gate Bonnet	3" -900 Lbs	Heat No.:	K48025
	Gate Wedge	3" -900 Lbs	Heat No.:	K48025


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANALISIS QUÍMICO - CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48025	0.061	0.78	1.25	0.022	0.031	18.63	9.56	0.017	0.71		3	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm ²	L. Elástico Yield Point N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48025	Lo = 4D	12.5	500	244	37	62	196	61	68	63
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

hereby certify that the material described above, has been tested and complies the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5882 to W5889
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 24
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp:	
		

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	3" -900 Lbs	Heat No.:	K48021
	Gate Bonnet	3" -900 Lbs	Heat No.:	K48021
	Gate Wedge	3" -900 Lbs	Heat No.:	K48021


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48021	0.049	0.66	1.32	0.019	0.020	18.24	9.21	0.016	0.57		24	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm ²	L. Elástico Yield Point N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48021	Lo = 4D	12.5	502	256	39	63	194	62	69	73
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados 3.1.B. correspondientes s/ EN 10204, que obran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are an exact transcription from the corresponding 3.1.B. certificates acc. to EN 10204, which are filed in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **100-S656-W5881**

Work Order: **W5881-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 3"**

Heat No.: **K48025**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: 100

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5881

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473
17 ENE. 2005

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

QA/QC Department

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **100-S656-W5882**

Work Order: **W5882-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 3"**

Heat No.: **K48021**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **100**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5882**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by **Level II SNT-TC-1A**
EN 473

Approved by **Level II SNT-TC-1A**
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 100-S656-W5883

Work Order: **W5883-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 3"**

Heat No.: **K48021**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **100**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5883**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 ENE

2005
Sign.

Sign.

Sign.

Date **January 17, 2005**

QA/QC Department

Date **January 17, 2005**

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 100-S656-W5884

Work Order: **W5884-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 3"**

Heat No.: **K48021**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: 100

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5884

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Temperature (°C): **15°C**

Developer Time (min.): **7-30**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by: **Level II SNT-TC-1A**
EN 473 17 ENE 2005

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **100-S656-W5885**

Work Order: **W5885-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 3"**

Heat No.: **K48021**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **100**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5885**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 100-S656-W5886

Work Order: W5886-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 900Lb 3"

Heat No.: K48021

Drawing: 1. 900Lb BW

Part: BW end

Item: 100

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5886

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Temperature (°C): 15°C

Developer Time (min.): 7-30

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by: SPECIALTY VALVES RESEARCH
Level II SNT-TC-1A
EN 473 17 ENE 2005 EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

QA/QC

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **100-S656-W5887**

Work Order: **W5887-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 3"**

Heat No.: **K48021**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **100**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5887**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 100-S656-W5888

Work Order: **W5888-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 3"**

Heat No.: **K48021**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **100**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5888**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A VALVES MANUFACTURER EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **100-S656-W5889**

Work Order: **W5889-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 3"**

Heat No.: **K48021**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **100**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5889**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by: **Level II SNT-TC-1A**
EN 473

Approved by: **Level II SNT-TC-1A**
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date **January 17, 2005**

Date **January 17, 2005**

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5881
-------------------	--------------	--------------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE	Extension of Test: BW-ENDS
Drawing : 900LB 3"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48025	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80		IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20		Material Thickness: 30		
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 4MIN		

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	A2	/	/	/	/	/	I	OK
R2	2-1		II	A1	/	/	/	/	/	II	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7		II	/	/	/	/	/	/	I	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48025
Contract:	HH-02536	Part No.	W5881
Drawing:	900LB 3"	Descriptions:	GATE

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1 -R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure: ASME B 16.34	Report No.: W5882
-------------------------	-------------------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE	Extension of Test: BW-ENDS
Drawing : 90OLB 3"	Radiographed at: Shop: ☒ ☐
Material : CF8C Heat Number: K48021	Field: ☐


X Rays KV : 7 RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80	IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.03/0.10	Material Thickness: 30		
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 4MIN	

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	B1	/	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	A2	/	/	/	/	/	II	OK
R7	7		II	/	/	CA1	/	/	/	I	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No:	W5882
Drawing:	900LB 3"	Descriptions:	GATE

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5883
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 3"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48021	


X Rays KV : 7	RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80		IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20		Material Thickness: 30		
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 4MIN		

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	CA2	/	/	/	II	OK
R3	3-4		II	/	/	CA2	/	/	/	II	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7		II	/	/	/	/	/	/	I	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAII
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No:	W5883
Drawing:	900LB 3"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.: W5884
------------	--------------	-------------------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 90OLB 3"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48021	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80		IQI: ASTM 1B
Screens Type and Thickness :		Pb,0.05/0.20		Material Thickness: 30
Density : 1.5-4.0	Source Film Distance :	600MM	Exposure Time:	4MIN

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	A1	/	/	/	/	/	I	OK
R6	6-5		II	/	/	CA2	/	/	/	II	OK
R7	7		II	/	/	/	/	/	/	I	OK
R8	8		II	/	/	CB2	/	/	/	II	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No:	W5884
Drawing:	90OLB 3"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5885
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 3"	Radiographed at: Shop: ☒ ☐
Material : CF8C Heat Number: K48021	Field: ☐


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80	IQI:	ASTM 1B
Screens Type and Thickness :		Pb,0.05/0.20	Material Thickness:	30
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time: 4MIN

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	B2	/	/	/	/	II	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	CA2	/	/	/	II	OK
R4	4-3		II	/	/	CA1	/	/	/	I	OK
R5	5-6		II	/	/	CA1	/	/	/	I	OK
R6	6-5		II	/	B2	/	/	/	/	II	OK
R7	7		II	/	/	/	/	/	/	I	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No:	W5885
Drawing:	900LB 3"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5886
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 3"	Radiographed at: Shop: ☒ /
Material : CF8C Heat Number: K48021	Field: ☐

X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80		IQI: ASTM 1B
Screens Type and Thickness :		Pb,0.05/0.20		Material Thickness: 30
Density : 1.5-4.0	Source Film Distance :	600MM		Exposure Time: 4MIN

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	A1	/	/	/	/	/	I	OK
R2	2-1		II	/	/	CA2	/	/	/	II	OK
R3	3-4		II	A1	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7		II	/	/	/	/	/	/	I	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.


SPECIALTY VALVES RESEARCH, S.A.
 VALVES MANUFACTURER
 14 ENE. 2005
 QA/QC Departament


 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No	W5886
Drawing:	900LB 3"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5887
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 3"	Radiographed at: Shop: ☐ / Field: ☐
Material : CF8C Heat Number: K48021	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80		IQI: ASTM 1B
Screens Type and Thickness :		Pb,0.05/0.20		Material Thickness: 30
Density : 1.5-4.0	Source Film Distance : 600MM		Exposure Time: 4MIN	

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7		II	/	/	CA2	/	/	/	II	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAII)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No:	W5887
Drawing:	900LB 3"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5888
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 3"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48021	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80		
Screens Type and Thickness :		Pb,0.05/0.20		
Density : 1.5-4.0		Source Film Distance : 600MM		Material Thickness: 30
Exposure Time: 4MIN				

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7		II	/	/	CA2	/	/	/	II	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No.	W5888
Drawing:	90OLB 3"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
PHONE:	+ (34) 94. 455. 51. 51
FAX:	+ (34) 94. 455. 51. 50
WEBB:	www.svrvalves.com
E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure: ASME B 16.34 Report No.: W5889

Page: 1 / 2

Customer :	KLAUS UNION	Contract:	HH-02536
Description :	GATE BODY	Extension of Test:	BW-ENDS
Drawing :	900LB 3"	Radiographed at: Shop:	☒
Material :	CF8C Heat Number: K48021	Field:	☐


X Rays KV	Γ RAYS	Isotope :	IR 192	Curies:	40	Focal Spot Size:	3x3
Film Type, Brand and Size :	KODAK AA400,360x50/360x80			IQI:	ASTM 1B		
Screens Type and Thickness :	Pb,0.05/0.20			Material Thickness:	30		
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time:	4MIN		

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	A2	/	/	/	/	/	II	OK
R5	5-6		II	/	B2	/	/	/	/	II	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7		II	/	/	CA2	/	/	/	II	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPA)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No.	W5889
Drawing:	900LB 3"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00110	1	Absperrschieber mit Handrad Gate valve with handwheel	3"	Cl.1500 BW 88,9 x 11,13	ASTM A 351 CF8C	Valve Ident - No.: "S 656" LPI 110-S656-W5890 RE 5890

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 375 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 275 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 275 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION GmbH & Co. KG**

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	<i>W. Glass</i>

Lurgi Job - No.: 69690-10
Lurgi OGC PO,- No.: 4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

**CERTIFICADO DE MATERIALES s/
MILL CERTIFICATE Acc. To**

Nº/Nr.: W5890

DATE: 14/12/04

SHEET:

Cliente/Client.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: **HH-02536**

Cantidad:

Quantity: 3

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

T. CONDICION
CONDITION T.T.

SOLUTION 1050 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

Gate Body

3" -1500 Lbs

Heat No.:

K48022

Gate Bonnet

3" -1500 Lbs

Heat No.:

K48022

Gate Wedge

3" -1500 Lbs

Heat No.:

K48022

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 351 CF8C

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS

COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V	Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48022	0.053	0.69	1.14	0.017	0.016	19.14	9.47	0.011	0.62		3	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48022	Lo = 4D	12.5	500	255	37	68	185	66	62	68
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

we hereby certify that the material described above, has been tested and complies the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.

Quality Control Department
VALVES MANUFACTURER

14 ENE. 2005

QA/QC Department



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 110-S656-W5890

Work Order: **W5890-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 1500Lb 3"**

Heat No.: **K48022**

Drawing: **1. 1500Lb BW**

Part: **BW end**

Item: 110

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5890

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Temperature (°C): 15°C

Developer Time (min.): 7-30

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign. 2005

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5890
------------	--------------	-------------	-------

Page: 1 / 2

Customer :	KLAUS UNION	Contract:	HH-02536
Description :	GATE BODY	Extension of Test:	BW-ENDS
Drawing :	1500LB 3"	Radiographed at:	Shop: ☒ ☐
Material :	CF8C Heat Number: K48022	Field:	☐

X Rays KV	Γ RAYS	Isotope :	IR 192	Curies:	40	Focal Spot Size:	3x3
Film Type, Brand and Size :	KODAK AA400,360x50/360x80				IQI:	ASTM 1B	
Screens Type and Thickness :	Pb,0.05/0.20				Material Thickness:	40-45	
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time:	4min 20 s		

Evaluation standard for steel castings radiographic examination (See Back)		Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form		ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	CA2	/	/	/	II	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7		II	/	/	/	/	/	/	I	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify taht material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.


SPECIALTY VALVES RESEARCH, S.A.
 VALVES MANUFACTURER
 14 ENE. 2005
 QA/QC Departament


 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIR
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	VALVES ENTREPRISE, S.L.	Heat:	K48022
Contract:	HH-02536	Part No.	W5890
Drawing:	1500LB 3"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00120	2	Absperrschieber mit Handrad Gate valve with handwheel	4"	Cl.900 BW 114,3 x 6,02	ASTM A 351 CF8C	Valve Ident - No.: "S 656" LIP 120-S656-W5891 120-S656-W5892 RE W5891 W5892

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 225 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 165 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 165 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION GmbH & Co. KG**

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glas*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	<i>W. Glass</i>

Lurgi Job - No.: 69690-10
Lurgi OGC PO,- No.: 4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

Zeugnis-Nr.	Cert. No.
-------------	-----------

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5891-W5892
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido N° Purchase Order: HH-02536	Cantidad: Quantity: 6
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	4" -900 Lbs	Heat No.:	K48019
	Gate Bonnet	4" -900 Lbs	Heat No.:	K48019
	Gate Wedge	4" -900 Lbs	Heat No.:	K48019


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS											N° de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48019	0.050	0.75	1.30	0.019	0.021	18.65	9.47	0.014	0.72		6	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48019	Lo = 4D	12.5	495	235	36	68	188	72	65	78
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

hereby certify that the material described above, has been tested and complies the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **120-S656-W5891**

Work Order: **W5891-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 4"**

Heat No.: **K48019**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **120**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5891**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by **Level II SNT-TC-1A**
EN 473

Approved by **Level II SNT-TC-1A**
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 ENE. 2005
Sign.

Sign.

Sign.

Date **January 17, 2005**

QA/QC Department
Date **January 17, 2005**

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **120-S656-W5892**

Work Order: **W5892-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 4"**

Heat No.: **K48019**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **120**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5892**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Approved by

WITNESS POINT CUSTOMER

Level II SNT-TC-1A
EN 473

Level II SNT-TC-1A
EN 473

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.: W5891
------------	--------------	-------------------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 90OLB 4"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48019	


X Rays KV : 7 RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80	IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20	Material Thickness: 30		
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 3MIN	

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	CA1	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7		II	/	/	/	/	/	/	I	OK
R8	8		II	/	/	CB2	/	/	/	II	OK
R9	9		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48019
Contract:	HH-02536	Part No.	W5891
Drawing:	900LB 4"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5892
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 4"	Radiographed at: Shop: ☒ ☐
Material : CF8C Heat Number: K48019	Field: ☐


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80		IQI: ASTM 1B
Screens Type and Thickness :		Pb,0.05/0.20		Material Thickness: 40
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time: 4MIN

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	CA2	/	/	/	II	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7		II	/	/	/	/	/	/	I	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48019
Contract:	HH-02536	Part No.	W5892
Drawing:	900LB 4"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	40	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00130	2	Absperrschieber mit Handrad Gate valve with handwheel	4"	Cl.1500 BW 114,3 x 13,49	ASTM A 351 CF8C	Valve Ident - No.: "S 656" LPI 130-S656-W5893 130-S656-W5894 RE W5893 W5894

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 375 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 275 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 275 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION GmbH & Co. KG**

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
--------------	------------

Seite / Page 1

Sachbearbeiter
W. Glass

W. Glass

W. Glass

W. Glass

Luraj Job - No.: **69690-10**

Lurgji OGC PO,- No.: 4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

Zeugnis-Nr.

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5893-W5894
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 6
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	4" -1500 Lbs	Heat No.:	K48021
	Gate Bonnet	4" -1500 Lbs	Heat No.:	K48021
	Gate Wedge	4" -1500 Lbs	Heat No.:	K48021


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48021	0.049	0.66	1.32	0.019	0.020	18.24	9.21	0.016	0.57		6	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48021	Lo = 4D	12.5	502	256	39	63	194	62	69	73
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.



()

()

()

()



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **130-S656-W5893**

Work Order: **W5893-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 1500Lb 4"**

Heat No.: **K48021**

Drawing: **1. 1500Lb BW**

Part: **BW end**

Item: **130**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5893**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by: **Level II SNT-TC-1A**
EN 473

Approved by: **Level II SNT-TC-1A**
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

17 ENE. 2005

Sign.

Sign.

Sign.

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **130-S656-W5894**

Work Order: **W5894-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 1500Lb 4"**

Heat No.: **K48021**

Drawing: **1. 1500Lb BW**

Part: **BW end**

Item: **130**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5894**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by **Level II SNT-TC-1A**
EN 473 17 FNE
Approved by **Level II SNT-TC-1A**
2005 EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date **January 17, 2005**

Date **January 17, 2005**

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5893
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 1500LB 4"	Radiographed at: Shop: ☐ ☒
Material : CF8C Heat Number: K48021	Field: ☐


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80	IQI: ASTM 1B	
Screens Type and Thickness :		Pb,0.05/0.20	Material Thickness: 50	
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time: 5MIN

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	CA1	/	/	/	I	OK
R7	7		II	/	B2	/	/	/	/	II	OK
R8	8		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPA)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No:	W5893
Drawing:	150OLB 4"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	50	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5894
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 1500LB 4"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48021	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80	IQI: ASTM 1B	
Screens Type and Thickness :		Pb,0.05/0.20	Material Thickness: 50	
Density : 1.5-4.0	Source Film Distance :	600MM	Exposure Time: 5MIN	

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	B2	/	/	/	/	II	OK
R6	6-5		II	/	/	CB2	/	/	/	II	OK
R7	7		II	/	/	/	/	/	/	I	OK
R8	8		II	/	/	CA2	/	/	/	II	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No:	W5894
Drawing:	150OLB 4"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R8	KODAK AA400	50	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt
Customer:

Bestell-Nr.: Lurgi Job - No.: 69690-10
Order no.: Lurgi OGC PO.-No.: 4567571-000/1.69690/136

Project Name : 2nd Zagros Methanol Plant - Iran

Auftrag-Nr.: HH - 02536
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00140	2	Absperrschieber mit Handrad Gate valve with handwheel	6"	Cl.900 BW 114,3 x 6,02	ASTM A 351 CF8C	Valve Ident - No.: " S 656 " LPI 140-S656-W5895 140-S656-W5896 RE W5895, W5896

Auslegung + Prüfung nach API 600 / API 598 / Nace MR 0175
Design and tests acc. to

Sicht- und Funktionsprüfung: o.k.
visual and functional test:

Festigkeits-/Dichtheitsprüfung: Festigkeit / shell test = 225 bar Wasser / water (60 sec)
strength-/tightness-test: Dichtheit Sitz / seat = 165 bar Wasser / water (60 sec)
Rückdichtung / backseat = 165 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: ohne Beanstandung !
result: no complaint !

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: Walter Glass

Anlage: Dokumentation gemäß Material-Dokumentationsdeckblatt
enclosure Documentation acc. to material cover sheet



Datum / Date	25.02.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	<i>W. Glass</i>

Lurgi Job - No.: 69690-10
Lurgi OGC PO,- No.: 4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

Pos.	Benennung	Spezifikation	Stück	Bauteil	Ident.-Nr.	Werkstoff	Hersteller	Chargen-Nr.	Probe	Zeugnis-Nr.
Item	Designation	Valve Ident - No.:	Pc.	Piece parts	Ident.-No.	Material	Manufacturer	Heat No.	Sample No.	Cert. No.

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5895-W5896
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 6
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	6" -900 Lbs	Heat No.:	K48019
	Gate Bonnet	6" -900 Lbs	Heat No.:	K48019
	Gate Wedge	6" -900 Lbs	Heat No.:	K48019


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48019	0.050	0.75	1.30	0.019	0.021	18.65	9.47	0.014	0.72		6	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm ²	L. Elástico Yield Point N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48019	Lo = 4D	12.5	495	235	36	68	188	72	65	78
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

we hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **140-S656-W5895**

Work Order: **W5895-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 6"**

Heat No.: **K48019**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **140**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5895**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A

EN 473

Approved by

Level II SNT-TC-1A

EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 140-S656-W5896

Work Order: **W5896-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 6"**

Heat No.: **K48019**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: 140

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5896

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A

EN 473

Approved by

Level II SNT-TC-1A

EN 473

WITNESS POINT CUSTOMER

☐ YES

☐ NOT

☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5895
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 6"	Radiographed at: Shop: ☒ ☐
Material : CF8C Heat Number: K48019	Field: ☐


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80		IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20		Material Thickness: 40		
Density : 1.5-4.0	Source Film Distance : 450MM	Exposure Time: 1min 20s		

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	CB2	/	/	/	II	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7-8		II	/	/	/	/	/	/	I	OK
R8	8-9		II	/	/	CA2	/	/	/	II	OK
R9	9-7		II	/	/	/	/	/	/	I	OK
R10	10		II	/	/	/	/	/	/	I	OK
R11	11		II	/	/	/	/	/	/	I	OK
R12	12		II	/	/	/	/	/	/	I	OK
R13	13		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify taht material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48019
Contract:	HH-02536	Part No:	W5895
Drawing:	900LB 6"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R13	KODAK AA400	35	IR 192	ASTM 1B	450MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5896
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 6"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48019	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80		IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20		Material Thickness: 35		
Density : 1.5-4.0	Source Film Distance : 450MM	Exposure Time: 1min 20s		

Evaluation standard for steel castings radiographic examination (See Back)		Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form		ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-1		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-3		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-5		II	/	/	/	/	/	/	I	OK
R7	7-8		II	/	/	/	/	/	/	I	OK
R8	8-9		II	/	/	/	/	/	/	I	OK
R9	9-7		II	/	/	/	/	/	/	I	OK
R10	10		II	/	/	/	/	/	/	I	OK
R11	11		II	/	/	/	/	/	/	I	OK
R12	12		II	/	/	/	/	/	/	I	OK
R13	13		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48019
Contract:	HH-02536	Part No.	W5896
Drawing:	90OLB 6"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R13	KODAK AA400	35	IR 192	ASTM 1B	450MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job – No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00150	4	Absperrschieber mit Handrad Gate valve with handwheel	2"	CI 600 BW 60,3 x 5,54	ASTM A 351 CF8C	Valve Ident – No.: "S 658" Geeignet für den Sauerstoffeinsatz Suitable for oxygen service LPI 150-S658-W5897 to W5900 RE W5897 to W5900

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 150 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 110 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 110 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION GmbH & Co. KG**

Werksachverständiger:

Manufacturer's authorized inspector:

Walter Glass

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	<i>Rally</i>

Lurgi Job - No.: 69690-10
Lurgi OGC PO,- No.: 4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

Zeugnis-Nr.	Cert. No.	W5897 to W5900
-------------	-----------	-------------------

**CERTIFICADO DE MATERIALES s/
MILL CERTIFICATE Acc. To**

Nº/Nr.: W5897-W5898-
W5899-W5900

DATE: 14/12/04

SHEET:

Cliente/Cliet.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: **HH-02536**

Cantidad:

Quantity: **12**

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

T. CONDICION
CONDITION T.T.

SOLUTION 1050 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

Gate Body

2" -600 Lbs

Heat No.:

6952

Gate Bonnet

2" -600 Lbs

Heat No.:

6952

Gate Wedge

2" -600 Lbs

Heat No.:

6952

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 351 CF8C

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS


COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V	Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
6952	0.062	0.79	1.25	0.024	0.026	18.54	9.44	0.018	0.62		12	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
6952	Lo = 4D	12.5	500	242	39	62	196	65	67	66
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

—hereby certify that the material described above, has been tested and complies the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.



C

C

C

C



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 150-S658-W5897

Work Order: **W5897-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb BW**

Part: **BW end**

Item: 150

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5897

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by **SPECIALTY VALVES RESEARCH**
Level II SNT-TC-1A
EN 473 **17 ENE. 2005**

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 150-S658-W5898

Work Order: W5898-06/12

Customer: KLAUS UNION

Valve Type: Gate Valve 600Lb 2"

Heat No.: 6952

Drawing: 1. 600Lb BW

Part: BW end

Item: 150

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5898

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Temperature (°C): 15°C

Developer Time (min.): 7-30

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Approved by

WITNESS POINT CUSTOMER

Level II SNT-TC-1A

Level II SNT-TC-1A

☐ YES ☐ NOT ☐ OTHERS

EN 473

17 EN 2005

EN 473

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 150-S658-W5899

Work Order: **W5899-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb BW**

Part: **BW end**

Item: 150

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5899

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 150-S658-W5900

Work Order: **W5900-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 600Lb 2"**

Heat No.: **6952**

Drawing: **1. 600Lb BW**

Part: **BW end**

Item: 150

P. O. No.: HH-02536

Quantity: 1

Serials No.: W5900

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A
EN 473

Approved by

Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
PHONE:	+ (34) 94. 455. 51. 51
FAX:	+ (34) 94. 455. 51. 50
WEBB:	www.svrvalves.com
E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5897
-------------------	--------------	--------------------	-------

Page: 1 / 2

Customer :	KLAUS UNION	Contract:	HH-02536
Description :	GATE	Extension of Test:	BW-ENDS
Drawing :	60OLB 2"	Radiographed at:	Shop: ☒ Field: ☐
Material :	CF8C Heat Number: 6952		


X Rays KV	7 RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :	KODAK AA400,360x50/360x80			IQT: ASTM 1B
Screens Type and Thickness :	Pb,0.05/0.20		Material Thickness:	20
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time: 2min

Evaluation standard for steel castings radiographic examination (See Back)		Acceptance Standard	
Sketch of geometric arrangement of radiographs and location markers in attached form		ASME B 16.34	

[illegible]

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER


ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
PHONE:	+ (34) 94. 455. 51. 51
FAX:	+ (34) 94. 455. 51. 50
WEBB:	www.svrvalves.com
E-mail:	webmaster@svrvalves.com


RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	6952
Contract:	HH-02536	Part No.	W5897
Drawing:	600LB 2"	Descriptions:	GATE

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R2	KODAK AA400	20	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****






 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	6952
Contract:	HH-02536	Part No.:	W5898
Drawing:	600LB 2"	Descriptions:	GATE

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shield
R1-R2	KODAK AA400	20	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
PHONE:	+ (34) 94. 455. 51. 51
FAX:	+ (34) 94. 455. 51. 50
WEBB:	www.svrvalves.com
E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5899
-------------------	--------------	--------------------	-------

Page: 1 / 2

Customer :	KLAUS UNION	Contract:	HH-02536
Description :	GATE	Extension of Test:	BW-ENDS
Drawing :	600LB 2"	Radiographed at:	Shop: ☒ ☐
Material :	CF8C Heat Number: 6952	Field:	☐


X Rays KV	7 RAYS	Isotope : IR 192	Curies:	40	Focal Spot Size:	3x3
Film Type, Brand and Size :	KODAK AA400,360x50/360x80			IQI:	ASTM 1B	
Screens Type and Thickness :	Pb,0.05/0.20			Material Thickness:	20	
Density :	1.5-4.0	Source Film Distance :	600MM		Exposure Time:	2min

Evaluation standard for steel castings radiographic examination (See Back)		Acceptance Standard	
Sketch of geometric arrangement of radiographs and location markers in attached form		ASME B 16.34	

[illegible]

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	6952
Contract:	HH-02536	Part No.:	W5899
Drawing:	600LB 2"	Descriptions:	GATE

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R2	KODAK AA400	20	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
PHONE:	+ (34) 94. 455. 51. 51
FAX:	+ (34) 94. 455. 51. 50
WEBB:	www.svrvalves.com
E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5900
-------------------	--------------	--------------------	-------

Page: 1 / 2

Customer :	KLAUS UNION	Contract:	HH-02536
Description :	GATE	Extension of Test:	BW-ENDS
Drawing :	60OLB 2"	Radiographed at:	Shop: ☒ ☐
Material :	CF8C Heat Number: 6952		Field: ☐


X Rays KV	7 RAYS	Isotope : IR 192	Curies:	40	Focal Spot Size:	3x3
Film Type, Brand and Size :	KODAK AA400,360x50/360x80			IQI:	ASTM 1B	
Screens Type and Thickness :	Pb,0.05/0.20		Material Thickness:	20		
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time:	2min	

Evaluation standard for steel castings radiographic examination (See Back)		Acceptance Standard	
Sketch of geometric arrangement of radiographs and location markers in attached form		ASME B 16.34	

[illegible]

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify taht material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	6952
Contract:	HH-02536	Part No.	W5900
Drawing:	600LB 2"	Descriptions:	GATE

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shieldi
R1-R2	KODAK AA400	20	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job – No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00160	1	Absperrschieber mit Getriebe Gate valve Gear operated	10"	CI 900 BW 273,0 x 12,7	ASTM A 351 CF8C	Valve Ident – No.: "S 657G" LPI 160-S657G-W5901 RE W5901

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 225 bar Wasser / water (120 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 165 bar Wasser / water (120 sec)*
Rückdichtung / backseat = 165 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (120 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	

Lurgi Job - No.: 69690-10
Lurgi OGC PO, - No.: 4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5901
		DATE: 14/12/04
		SHEET: Rev.01

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 3
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--------------------------------	------------------	--

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	10" -900 Lbs	Heat No.:	K48058
	Gate Bonnet	10" -900 Lbs	Heat No.:	K48058
	Gate Wedge	10" -900 Lbs	Heat No.:	K48058


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48058	0.059	0.82	1.19	0.020	0.021	18.42	9.33	0.019	0.69		3	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm ²	L. Elástico Yield Point N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48058	Lo = 4D	12.5	505	255	40	66	198	67	69	75
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados 3.1.B. correspondientes s/ EN 10204, que obran en nuestro poder, emitidos por los suministradores homologados.

—hereby certify that the material described above, has been tested and complies the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding 3.1.B. certificates acc. to EN 10204, which are field in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **160-S657G-W5901**

Work Order: **W5901-06/12**
Customer: **KLAUS UNION**
Valve Type: **Gate Valve 900Lb 10"**
Heat No.: **K48058**
Drawing: **1. 900Lb BW**
Part: **BW end**

Item: **160**
P. O. No.: **HH-02536**
Quantity: **1**
Serials No.: **W5901**
Surface Conditions: **AS RAW**
Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473
17 FEB 2005

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5901
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 10"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48058	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80		IQT: ASTM 1B
Screens Type and Thickness :		Pb,0.05/0.20		Material Thickness: 50-55
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time: 5min

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-3		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-1		II	/	/	CB2	/	/	/	II	OK
R5	5-6		II	/	/	CA2	/	/	/	II	OK
R6	6-7		II	/	/	/	/	/	/	I	OK
R7	7-8		II	/	/	/	/	/	/	I	OK
R8	8-5		II	/	/	/	/	/	/	I	OK
R9	9-10		II	/	/	/	/	/	/	I	OK
R10	10-11		II	/	/	/	/	/	/	I	OK
R11	11-12		II	/	/	/	/	/	/	I	OK
R12	12-13		II	/	/	/	/	/	/	I	OK
R13	13-11		II	/	/	/	/	/	/	I	OK
R14	14		II	/	/	/	/	/	/	I	OK
R15	15		II	/	/	CB3	/	/	/	III	OK
R16	16		II	/	/	CB2	/	/	/	II	OK
R17	17		II	/	/	/	/	/	/	I	OK

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48058
Contract:	HH-02536	Part No:	W5901
Drawing:	900LB 10"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R17	KODAK AA400	50-55	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job – No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00170	2	Absperrschieber mit Getriebe Gate valve Gear operated	12"	CI 900 BW 323,9 x 12,7	ASTM A 351 CF8C	Valve Ident – No.: " S 657G " LPI 170-S657G-W5902 170-S657G-W5903 RE W5902, W5903

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 225 bar Wasser / water (300 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 165 bar Wasser / water (120 sec)*
Rückdichtung / backseat = 165 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (120 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*

○

○

○

○



HH-02536

Project Name: 2nd Zagros Methanol Plant - Iran

Sachbearbeiter
Person in charge

W. Glass

W. Glass
Wall GB

28.02.2005

**CERTIFICADO DE MATERIALES s/
MILL CERTIFICATE Acc. To**

Nº/Nr.: W5902

DATE: 14/12/04

SHEET:

Cliente/Cliet.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº
Purchase Order: **HH-02536**

Cantidad:
Quantity: **3**

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

T. CONDICION
CONDITION T.T.

SOLUTION 1050 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

Gate Body

12" -900 Lbs

Heat No.:

K48020

Gate Bonnet

12" -900 Lbs

Heat No.:

K48020

Gate Wedge

12" -900 Lbs

Heat No.:

K48020

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 351 CF8C

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS

COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00				
K48020	0.047	0.66	1.24	0.021	0.023	18.25	9.16	0.017	0.55			3	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48020	Lo = 4D	12.5	502	240	38	67	195	68	63	61
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.

Quality Control Department

14 ENE. 2005


QA/QC Departament

○

○

○

○

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5903
		DATE: 14/12/04
		SHEET:

Cliente/Client.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 3
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	


TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	12" -900 Lbs	Heat No.:	K48021
	Gate Bonnet	12" -900 Lbs	Heat No.:	K48020
	Gate Wedge	12" -900 Lbs	Heat No.:	K48020


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48021	0.049	0.66	1.32	0.019	0.020	18.24	9.21	0.016	0.57		1	
K48020	0.047	0.66	1.24	0.021	0.023	18.25	9.16	0.017	0.55		2	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48021	Lo = 4D	12.5	502	256	39	63	194	62	69	73
K48020	Lo = 4D	12.5	502	240	38	67	195	68	63	61
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gamma-graphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

Hereby certify that the material described above, has been tested and complies with material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.







SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **170-S657G-W5902**

Work Order: **W5902-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 12"**

Heat No.: **K48020**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **170**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5902**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by

Level II SNT-TC-1A
EN 473

Approved by

Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

2

3

4

5



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **170-S657G-W5903**

Work Order: **W5903-06/12**
Customer: **KLAUS UNION**
Valve Type: **Gate Valve 900Lb 12"**
Heat No.: **K48021**
Drawing: **1. 900Lb BW**
Part: **BW end**

Item: 170
P. O. No.: HH-02536
Quantity: 1
Serials No.: W5903
Surface Conditions: AS RAW
Material: ASTM A351 CF8C

Reference Procedure: **E165**
Acceptance Standards: **ANSI B 16.34**
Precleaned by: **WATER**
Type of penetrant: **HP-ST**
Rinsed by: **HD-ST**
Type of developer: **HR-ST**
Penetr. Time (min.): **5-20**
Temperature (°C): **15°C**

Developer Time (min.): **7-30**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by **SPECIALTY VALVES RESEARCH, S.A.**
Level II SNT-TC-1A
EN 473 17 FNE 2005

WITNESS POINT CUSTOMER
☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5902
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 12"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48020	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80	IQI: ASTM 1B	
Screens Type and Thickness :		Pb,0.05/0.20	Material Thickness: 50-55	
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time: 5min-5min 20s

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-3		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-5		II	/	/	/	/	/	/	II	OK
R5	5-1		II	/	/	/	/	/	/	II	OK
R6	6-7		II	/	/	/	/	/	/	I	OK
R7	7-8		II	/	/	/	/	/	/	I	OK
R8	8-9		II	/	/	/	/	/	/	I	OK
R9	9-10		II	/	/	/	/	/	/	I	OK
R10	10-6		II	/	/	/	/	/	/	I	OK
R11	11-12		II	/	/	CA2	/	/	/	I	OK
R12	12-13		II	/	/	CB2	/	/	/	I	OK
R13	13-14		II	/	/	CB2	/	/	/	I	OK
R14	14-15		II	/	/	/	/	/	/	I	OK
R15	15-11		II	/	/	/	/	/	/	III	OK
R16	16		II	/	/	/	/	/	/	II	OK
R17	17		II	/	/	/	/	/	/	I	OK
R18	18		II	/	/	/	/	/	/	I	OK
R19	19		II	/	/	/	/	/	/	I	OK
R20	20		II	/	/	/	/	/	/	I	OK
R21	21		II	/	/	/	/	/	/	I	OK

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory. emitted by homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER


ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
PHONE:	+ (34) 94. 455. 51. 51
FAX:	+ (34) 94. 455. 51. 50
WEBB:	www.svrvalves.com
E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48020
Contract:	HH-02536	Part No.	W5902
Drawing:	900LB 12"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R21	KODAK AA400	50-55	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5903
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 12"	Radiographed at: Shop: ☒ ☐
Material : CF8C Heat Number: K48021	Field: ☐


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80	IQT: ASTM 1B	
Screens Type and Thickness :		Pb,0.05/0.20	Material Thickness: 50-55	
Density :	1.5-4.0	Source Film Distance :	600MM	Exposure Time: 5min-5min 20s

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-3		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-5		II	/	/	/	/	/	/	I	OK
R5	5-1		II	/	/	/	/	/	/	I	OK
R6	6-7		II	/	/	/	/	/	/	I	OK
R7	7-8		II	/	/	/	/	/	/	I	OK
R8	8-9		II	/	/	/	/	/	/	I	OK
R9	9-10		II	/	/	/	/	/	/	I	OK
R10	10-6		II	/	/	/	/	/	/	I	OK
R11	11-12		II	/	/	/	/	/	/	I	OK
R12	12-13		II	/	/	/	/	/	/	I	OK
R13	13-14		II	/	/	/	/	/	/	I	OK
R14	14-15		II	/	/	/	/	/	/	I	OK
R15	15-11		II	/	/	/	/	/	/	I	OK
R16	16		II	/	/	CA2	/	/	/	I	OK
R17	17		II	/	/	/	/	/	/	I	OK
R18	18		II	/	/	/	/	/	/	I	OK
R19	19		II	/	/	/	/	/	/	I	OK
R20	20		II	/	/	/	/	/	/	I	OK
R21	21		II	/	/	/	/	/	/	I	OK

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48021
Contract:	HH-02536	Part No.	W5903
Drawing:	900LB 12"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R21	KODAK AA400	50-55	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00180	2	Absperrschieber mit Antrieb Gate valve Gear operated	16"	CI 600 BW 406,4 x 12,7	ASTM A 351 CF8C	Valve Ident - No.: "S 657G" LPI 180-S657G-W5904 180-S657G-W5905 RE W 5904, W5905

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 150 bar Wasser / water (300 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 110 bar Wasser / water (120 sec)*
Rückdichtung / backseat = 110 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (120 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*

()

()

()

()



Datum / Date	25.02.2005
--------------	------------

Seite / Page 1

W Glass

W. Glass
Walter J. J.

Lurgi Job - No.: 69690-10
Lurgi OGC PO- No.: 4567571 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

Chargen-Nr.	Probe	Zeugnis-Nr.
Heat No.	Sample No.	Cert. No.

**CERTIFICADO DE MATERIALES s/
MILL CERTIFICATE Acc. To**

Nº/Nr.: W5904

DATE: 14/12/04

SHEET:

Cliente/Cliet.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: **HH-02536**

Cantidad:

Quantity: 3

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

T. CONDICION
CONDITION T.T.

SOLUTION 1050 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

Gate Body

16" -600 Lbs

Heat No.:

K48014

Gate Bonnet

16" -600 Lbs

Heat No.:

K48009

Gate Wedge

16" -600 Lbs

Heat No.:

K48009

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 351 CF8C

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS

COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V	Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48014	0.059	0.79	1.26	0.018	0.020	19.36	9.28	0.019	0.58		1	
K48009	0.046	1.06	1.26	0.023	0.019	18.62	10.06	0.023	0.62		2	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48014	Lo = 4D	12.5	512	246	39	69	185	68	67	66
K48009	Lo = 4D	12.5	490	225	39	68	188	60	64	63
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammaografia Gammaographic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

we hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.

Quality Control Department
VALVES MANUFACTURER
14 ENE. 2005
QA/QC Departament

()

()

()

()

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W5905
		DATE: 14/12/04
		SHEET:

Cliente/Cliet.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536	Cantidad: Quantity: 3
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	16" -600 Lbs	Heat No.:	K48015
	Gate Bonnet	16" -600 Lbs	Heat No.:	K48009
	Gate Wedge	16" -600 Lbs	Heat No.:	K48009


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------

ANÁLISIS QUÍMICO – CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48015	0.051	1.23	0.89	0.021	0.018	18.2	9.6	0.024	0.78		1	
K48009	0.046	1.06	1.26	0.023	0.019	18.62	10.06	0.023	0.62		2	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C		
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60		
K48015	Lo = 4D	12.5	490	250	36	65	185	63	69	64
K48009	Lo = 4D	12.5	490	225	39	68	188	60	64	63
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

_____ hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.







SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **180-S657G-W5904**

Work Order: **W5904-06/12**
Customer: **KLAUS UNION**
Valve Type: **Gate Valve 600Lb 16"**
Heat No.: **K48014**
Drawing: **1. 600Lb BW**
Part: **BW end**

Item: **180**
P. O. No.: **HH-02536**
Quantity: **1**
Serials No.: **W5904**
Surface Conditions: **AS RAW**
Material: **ASTM A351 CF8C**

Reference Procedure: **E165**
Acceptance Standards: **ANSI B 16.34**
Pecleaned by: **WATER**
Type of penetrant: **HP-ST**
Rinsed by: **HD-ST**
Type of developer: **HR-ST**
Penetr. Time (min.): **5-20**
Temperature (°C): **15°C**

Developer Time (min.): **7-30**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **180-S657G-W5905**

Work Order: **W5905-06/12**
Customer: **KLAUS UNION**
Valve Type: **Gate Valve 600Lb 16"**
Heat No.: **K48015**
Drawing: **1. 600Lb BW**
Part: **BW end**

Item: **180**
P. O. No.: **HH-02536**
Quantity: **1**
Serials No.: **W5905**
Surface Conditions: **AS RAW**
Material: **ASTM A351 CF8C**

Reference Procedure: **E165**
Acceptance Standards: **ANSI B 16.34**
Pecleaned by: **WATER**
Type of penetrant: **HP-ST**
Rinsed by: **HD-ST**
Type of developer: **HR-ST**
Penetr. Time (min.): **5-20**
Temperature (°C): **15°C**

Developer Time (min.): **7-30**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by **SPECIALTY VALVES RESEARCH, S.A.**
Level II SNT-TC-1A
EN 473 17 ENE. 2005 **EN 473**

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

QA/OC

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure: ASME B 16.34	Report No.: W5904
--------------------------------	--------------------------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 600LB 16"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48014	


X Rays KV 17 RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80		IQT: ASTM 1B	
Screens Type and Thickness : Pb,0.05/0.20		Material Thickness: 60-68	
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 6min	

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-3		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-5		II	/	/	/	/	/	/	I	OK
R5	5-1		II	/	/	/	/	/	/	I	OK
R6	6-7		II	/	/	/	/	/	/	I	OK
R7	7-8		II	/	/	/	/	/	/	I	OK
R8	8-9		II	/	/	/	/	/	/	I	OK
R9	9-10		II	/	/	/	/	/	/	I	OK
R10	10-6		II	/	/	/	/	/	/	I	OK
R11	11-12		II	/	/	/	/	/	/	I	OK
R12	12-13		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

ADDRESS:

ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)

PHONE:

+ (34) 94. 455. 51. 51

FAX:

+ (34) 94. 455. 51. 50

WEBB:

www.svrvalves.com

E-mail:


webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48014
Contract:	HH-02536	Part No.	W5904
Drawing:	600LB 16"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R12	KODAK AA400	60-68	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W5905
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 600LB 16"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48015	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size :		KODAK AA400,360x50/360x80		IQI: ASTM 1B
Screens Type and Thickness :		Pb,0.05/0.20		Material Thickness: 60-68
Density : 1.5-4.0	Source Film Distance :	600MM		Exposure Time: 6min

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-3		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-5		II	/	/	/	/	/	/	I	OK
R5	5-1		II	/	/	/	/	/	/	I	OK
R6	6-7		II	/	/	CA2	/	/	/	II	OK
R7	7-8		II	/	/	/	/	/	/	I	OK
R8	8-9		II	/	/	/	/	/	/	I	OK
R9	9-10		II	/	/	/	/	/	/	I	OK
R10	10-6		II	/	/	/	/	/	/	I	OK
R11	11-12		II	/	/	/	/	/	/	I	OK
R12	12-13		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.




 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48015
Contract:	HH-02536	Part No.	W5905
Drawing:	600LB 16"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shield
R1-R12	KODAK AA400	60-68	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****



Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job – No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00190	1	Absperrschieber mit Antrieb Gate valve Gear operated	16"	CI 900 BW 406,4 x 16,6	ASTM A 351 CF8C	Valve Ident – No.: "S 657G" LPI 190-S657G-W5906 RE W5906

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 225 bar Wasser / water (300 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 165 bar Wasser / water (120 sec)*
Rückdichtung / backseat = 165 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (120 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*



Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*

1

2

3

4



Datum / Date	25.02.2005
--------------	------------

Seite / Page
1

W. Glass
Wally GB

Walter Sp

Lurji OGC PO - No: 4567571 - 000 / 1 69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

28.02.2005

()

()

()

()



CERTIFICADO DE MATERIALES s/
MILL CERTIFICATE Acc. To

Nº/Nr.: W5906

DATE: 14/12/04

SHEET:

Cliente/Cient.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: HH-02536

Cantidad:

Quantity: 3

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

H.T. CONDICION
CONDITION T.T.

SOLUTION 1050 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

Gate Body

16" -900 Lbs

Heat No.:

K48016

Gate Bonnet

16" -900 Lbs

Heat No.:

K48016

Gate Wedge

16" -900 Lbs

Heat No.:

K48016

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 351 CF8C

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS


COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V	Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
K48016	0.046	1.06	1.26	0.023	0.019	18.62	10.06	0.023	0.61		3	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20°C
Solicitado Requirements	Lo = 4D	12.5	485	205	.30		232	60
K48016	Lo = 4D	12.5	490	225	39	65	195	66 65 68
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test
S/ MSS-SP-55		Satisfactory						

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados 3.1.B. correspondientes s/ EN 10204, que obran en nuestro poder, emitidos por los suministradores homologados.

— hereby certify that the material described above, has been tested and complies with the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding 3.1.B. certificates acc. to EN 10204, which are field in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **190-S657G-W5906**

Work Order: **W5906-06/12**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 900Lb 16"**

Heat No.: **K48016**

Drawing: **1. 900Lb BW**

Part: **BW end**

Item: **190**

P. O. No.: **HH-02536**

Quantity: **1**

Serials No.: **W5906**

Surface Conditions: **AS RAW**

Material: **ASTM A351 CF8C**

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473
17 ENE. 2005

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 17, 2005

Date January 17, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No. :	W5906
------------	--------------	--------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 900LB 16"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48016	


X Rays KV : 7 RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x50/360x80	IQI: ASTM 1B		
Screens Type and Thickness : Pb,0.05/0.20	Material Thickness: 50-70		
Density : 1.5-4.0	Source Film Distance : 600MM	Exposure Time: 5min 30s-7min	

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-3		II	/	/	/	/	/	/	I	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-5		II	/	/	/	/	/	/	I	OK
R5	5-1		II	/	/	/	/	/	/	I	OK
R6	6-7		II	/	/	/	/	/	/	II	OK
R7	7-8		II	/	/	/	/	/	/	I	OK
R8	8-9		II	/	/	/	/	/	/	I	OK
R9	9-10		II	/	/	/	/	/	/	I	OK
R10	10-6		II	/	/	/	/	/	/	I	OK
R11	11		II	/	/	/	/	/	/	I	OK
R12	12		II	/	/	CA2	/	/	/	II	OK
R13	13		II	/	/	/	/	/	/	I	OK
R14	14		II	/	/	/	/	/	/	I	OK
R15	15		II	/	/	/	/	/	/	I	OK
R16	16		II	/	/	/	/	/	/	I	OK
R17	17-18		II	/	/	/	/	/	/	I	OK
R18	18-19		II	/	/	/	/	/	/	I	OK
R19	19-20		II	/	/	/	/	/	/	I	OK
R20	20-21		II	A2	/	/	/	/	/	II	OK
R21	21-22		II	/	/	/	/	/	/	I	OK
R22	22-17		II	/	/	CB2	/	/	/	II	OK

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated



are exact transcription from the corresponding certificates, which are filed in our factory, emitted by homologated suppliers.


 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48016
Contract:	HH-02536	Part No.	W5906
Drawing:	900LB 16"	Descriptions:	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1-R22	KODAK AA400	50-55	IR 192	ASTM 1B	600MM	1.5-3.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: **Lurgi AG, D-60295 Frankfurt**
Customer:

Bestell-Nr.: **Lurgi Job - No.: 69690-10**
Order no.: **Lurgi OGC PO.-No.: 4567571-001/1.69690/145**

Project Name : **2nd Zagros Methanol Plant - Iran**

Auftrag-Nr.: **HH - 02536- 02**
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00220	2	Absperrschieber mit Handrad Gate valve with handwheel	2"	Cl.300 RF	ASTM A 351 CF8C	Valve Ident - No.: " S 655 " LPI S1276 / S1277

Auslegung + Prüfung nach **API 600 / API 598 / Nace MR 0175**
Design and tests acc. to

Sicht- und Funktionsprüfung: **o.k.**
visual and functional test:

Festigkeits-/Dichtheitsprüfung: **Festigkeit / shell test = 75 bar Wasser / water (60 sec)**
strength-/tightness-test: **Dichtheit Sitz / seat = 55 bar Wasser / water (60 sec)**
Rückdichtung / backseat = 55 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: **ohne Beanstandung !**
result: **no complaint !**



Bochum, den 16.09.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: **Walter Glass**

Anlage: **Dokumentation gemäß Material-Dokumentationsdeckblatt**
enclosure **Documentation acc. to material cover sheet**

()

()

()

()



Datum / Date	16.09.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	

Lurgi Job - No.: **69690-10**
Lurgi OGC PO- No.: **4567571 - 001 / 1.69690 / 145**

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES MILL CERTIFICATE	Nº/Nr.: S1276-S1277
		FECHA:
		DATE: 24-06-05

Cliente/Cient.: Klaus Union Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536-02	Cantidad: Quantity: 6
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp:	
		

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Quenched+Tempered:	Solution:	

H.T. CONDICION CONDITION T.T.	Solution 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	GATE BODY	2" – 300 Lbs	Heat No.:	8040
	GATE BONNET	2" – 300 Lbs	Heat No.:	8040
	GEAT WEDGE	2" – 300 Lbs	Heat No.:	Y040


CALIDAD DE ACERO: STEEL QUALITY:	ASTM A351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	----------------	---	------------------

ANÁLISIS QUÍMICO – CHEMICAL ANALYSIS												Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	V			
Solicitado (Norma) Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	0.50	9.0- 12.0					
8040	0.052	1.38	0.78	0.021	0.020	19.8	0.025	10.5				4	
Y040	0.045	1.21	0.65	0.020	0.022	20.2	0.028	9.36				2	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	Resistencia Tensile Str. N/mm²	L. Elástico Yield Point N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20 °C		
Solicitado Requirements	Lo = 4D	12.5	485	205	30	60	232	60		
8040	Lo = 4D	12.5	510	228	38	65	165	65	62	68
Y040	Lo = 4D	12.5	495	285	39	68	170	65	67	62
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B.** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, has been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: **S1276**

Work Order: **S1276**

Customer: **KLAUS UNION**

Valve Type: **Gate Valve 300Lb 2"**

Heat No.: **8040**

Drawing: **1. 300Lb RF**

Part: **Flange end**

Item: 00220

P. O. No.: HH-02536-02

Quantity: 1

Serials No.: S1276

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: **E165**

Acceptance Standards: **ANSI B 16.34**

Precleaned by: **WATER**

Type of penetrant: **HP-ST**

Rinsed by: **HD-ST**

Type of developer: **HR-ST**

Penetr. Time (min.): **5-20**

Developer Time (min.): **7-30**

Temperature (°C): **15°C**

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date 05-08-2005

QA/QC Departament
Date 05-08-2005

Date

Date



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: S1277

Work Order: **S1277**
Customer: **KLAUS UNION**
Valve Type: **Gate Valve 300Lb 2"**
Heat No.: **8040**
Drawing: **1. 300Lb RF**
Part: **Flange end**

Item: 00220
P. O. No.: HH-02536-02
Quantity: 1
Serials No.: S1277
Surface Conditions: AS RAW
Material: ASTM A351 CF8C

Reference Procedure: **E165**
Acceptance Standards: **ANSI B 16.34**
Precleaned by: **WATER**
Type of penetrant: **HP-ST**
Rinsed by: **HD-ST**
Type of developer: **HR-ST**
Penetr. Time (min.): 5-20
Temperature (°C): 15°C

Developer Time (min.): 7-30

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:

RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

- ☐ Accepted
☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.
QA/QC Department

Sign.

Sign.

Date 05-08-2005

Date 05-08-2005

Date

Date

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi AG, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4567571-002/1.69690/145*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536- 03*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00230	1	Absperrschieber mit Handrad Gate valve with handwheel	3"	Cl.300 RF	A 216 WCB	Valve Ident - No.: "S 360" S1549

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 75 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 55 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 55 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 10.10.2005 - WG **KLAUS UNION** GmbH & Co. KG

Werksachverständiger:

Manufacturer's authorized inspector: *Walter Glass*



Walter Glass

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	10.10.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	

Datum / Date	10.10.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	

Lurgi Job - No.: 69690-10
Lurgi OGC PO,- No.: 4567571 - 002 / 1.69690 / 145

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES MILL CERTIFICATE	N°/Nr.: S1549 FECHA: DATE: 12-08-05
--	---	---

Cliente/Cliet.: Klaus Union Armaturen International Bremer Str. 53 D-21244 Buchholz	<table style="width:100%;"> <tr> <td style="width:50%;"> Pedido N° Purchase Order: HH-02536-03 </td> <td style="width:50%;"> Cantidad: Quantity: 3 </td> </tr> <tr> <td colspan="2" style="text-align: center;"> Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp:  </td> </tr> </table>	Pedido N° Purchase Order: HH-02536-03	Cantidad: Quantity: 3	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 	
Pedido N° Purchase Order: HH-02536-03	Cantidad: Quantity: 3				
Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp: 					

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☒	Normalizado+Revenido ☐	Templado+Revenido: ☐	Solubilización: ☐
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

H.T. CONDICION CONDITION T.T.	Normalized 980°C × 3h	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	-----------------------	--

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	GATE BODY	300LB-3"	Heat No.:	9828
	GATE BONNET	300LB-3"	Heat No.:	9810
	GATE WEDGE	300LB-3"	Heat No.:	Y988

CALIDAD DE ACERO: STEEL QUALITY:	ASTM A216 WCB	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	---------------	---	------------------


ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS											N° de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	V		
Solicitado (Norma) Requirements (max)	0.30	0.60	1.00	0.040	0.045	0.5	0.50	0.20	0.30	0.03		
9828	0.22	0.33	0.76	0.023	0.019	0.06	0.022	0.003	0.030	0.007	1	
9810	0.20	0.38	0.80	0.020	0.021	0.07	0.019	0.017	0.016	0.001	1	
Y988	0.21	0.35	0.72	0.019	0.020	0.06	0.018	0.019	0.014	0.001	1	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	L. Elástico Yield Point N/mm²	Resistencia Tensile Str. N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J: T 20 °C		
Solicitado Requirements	Lo = 4D	12.5	250	485-655	22	35	232	27 J		
9828	Lo = 4D	12.5	285	485	28	38	150	42	28	36
9810	Lo = 4D	12.5	290	490	29	39	152	35	30	41
Y988	Lo = 4D	12.5	305	510	31	42	155	45	44	32
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammaographic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados 3.1.B correspondientes a EN 10204, que obran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, has been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding 3.1.B. certificates acc. to EN 10204, which are held in our factory, emitted by our homologated suppliers.

Quality Control Department





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: Lurgi AG, D-60295 Frankfurt
Customer:

Bestell-Nr.: Lurgi Job - No.: 69690-10
Order no.: Lurgi OGC PO.-No.: 4567571-002/1.69690/145

Project Name : 2nd Zagros Methanol Plant - Iran

Auftrag-Nr.: HH - 02536- 03
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00240	1	Absperrschieber mit Handrad Gate valve with handwheel	2"	Cl.1500 BW	A 217 WC6	Valve Ident - No.: "S 421" LPI S1550

Auslegung + Prüfung nach API 600 / API 598 / Nace MR 0175
Design and tests acc. to

Sicht- und Funktionsprüfung: o.k.
visual and functional test:

Festigkeits-/Dichtheitsprüfung: Festigkeit / shell test = 375 bar Wasser / water (60 sec)
strength-/tightness-test: Dichtheit Sitz / seat = 275 bar Wasser / water (60 sec)
Rückdichtung / backseat = 275 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: ohne Beanstandung !
result: no complaint !

Bochum, den 10.10.2005 - WG KLAUS UNION GmbH & Co. KG
Werksachverständiger:

Manufacturer's authorized inspector: Walter Glass



Walter Glass

Anlage: Dokumentation gemäß Material-Dokumentationsdeckblatt
enclosure Documentation acc. to material cover sheet



Materialdokumentations - Deckblatt

Material Cover Sheet

Datum / Date	10.10.2005
Seite / Page	1
Sachbearbeiter	W. Glass
Person in charge	

**Kommissions-Nr. /
Reference No.**

Lurgi Job - No.: 69690-10
Lurgi OGC PO.- No.: 4567571 - 002 / 1.69690 / 145

HH-02536-03

Project Name: 2nd Zagros Methanol Plant - Iran

[illegible]

20.10.2005



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

CERTIFICADO DE MATERIALES MILL CERTIFICATE

Nº/Nr.: S1550

FECHA:

DATE: 12-08-05

Cliente/Client.:

Klaus Union
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: HH-02536-03

Cantidad:

Quantity: 3

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



TRATAMIENTO TERMICO
HEAT TREATMENT

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

H.T. CONDICION
CONDITION T.T.

NORMALIZED 980 °C x 3H+Tempered 630 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:

GATE BODY

1500LB-2"

Heat No.:

K53623

GATE BONNET

1500LB-2"

Heat No.:

9860

GATE WEDGE

1500LB-2"

Heat No.:

Y988

CALIDAD DE ACERO:
STEEL QUALITY:

ASTM A 217 WC6

CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:

NACE MR 01-75:00

ANALISIS QUÍMICO - CHEMICAL ANALYSIS

COLADA HEAT No.	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	W		Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado (Norma) Requirements (max)	0.05- 0.20	0.60	0.50- 0.80	0.040	0.045	1.00- 1.50	0.50	0.45- 0.65	0.50	0.10			
K53623	0.12	0.42	0.65	0.021	0.025	1.25	0.028	0.52	0.027	0.001		1	
9860	0.18	0.37	0.72	0.022	0.027	1.08	0.025	0.55	0.035	0.001		1	
Y988	0.16	0.45	0.66	0.018	0.031	1.36	0.032	0.49	0.045	0.001		1	


PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	L. Elástico Yield Point N/mm²	Resistencia Tensile Str. N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20 °C		
Solicitado Requirements	Lo = 4D	12.5	275	485-655	20	35	232	27 J		
K53623	Lo = 4D	12.5	295	495	25	37	162	40	45	38
9860	Lo = 4D	12.5	325	525	32	45	165	43	42	30
Y988	Lo = 4D	12.5	285	498	29	39	160	39	34	38
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados 3.1.B. correspondientes a EN 10204, que obran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, has been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding 3.1.B. certificates acc. to EN 10204, which are filed in our factory, emitted by our homologated suppliers.

Quality Control Department



○

○

○

○



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: S1550

Work Order: S1550-11/08

Customer: VALVES ENTREPRISE

Valve Type: Gate Valve 1500Lb 2"

Heat No.: K53623

Drawing: 1. 1500Lb BW

Part: BW end

Item: 00240

P. O. No.: HH-02536-03

Quantity: 1

Serials No.: S1550

Surface Conditions: AS RAW

Material: ASTM 217 WC6

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HD-RS

Rinsed by: HD-BX

Type of developer: HD-YS

Penetr. Time (min.): 5-20




Developer Time (min.): 7-30

Temperature (°C): 25°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of
Discontinuities:



RESULTS:

- ☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date 21/09/2005

Date 21/09/2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure: **ASME B 16.34** Report No.: **S 1550**


Page: 1 / 2

Customer:	VALVES ENTREPRISE, S.L.	Contract:	HH-02536-03
Description:	GATE BODY	Extension of Test:	BW-ENDS
Drawing:	1500LB 2"	Radiographed at:	Shop: ☒ / Field: ☐
Material:	WC6 Heat Number: K53623		

X-Rays KV:	Γ RAYS	Isotope:	IR 192	Curies:	50	Focal Spot Size:	2x2
Film Type, Brand and Size:	AGFAC7, 360x80			IQI:	ASTM 18		
Screens Type and Thickness:	Pb,0.05/0.20			Material Thickness:	Thickness+2mm		
Density:	1.5-3.5	Source Film Distance:	300MM	Exposure Time:	75Ci/5s		

Evaluation standard for steel castings radiographic examination (See Back)		Acceptance Standard:
Sketch of geometric arrangement of radiographs and location markers in attached form		ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
S1550-1	1		II	/	/	/	/	/	/	I	OK
S1550-2	2		II	/	/	/	/	/	/	I	OK
S1550-3	3		II	/	/	/	/	/	/	I	OK
S1550-4	4		II	/	/	/	/	/	/	I	OK
S1550-5	5-6		II	/	B1	/	/	/	/	I	OK
S1550-6	6-5		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados. We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.	
--	--


 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure	ASME B 16.34		
Customer	VALVES ENTREPRISE, S.L.	Heat	K53623
Contract	HH-02536-03	Part No	S 1550
Drawing	1500LB 2"	Descriptions	GATE BODY

Radiography No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
CI - C8	AGFACT, 360x80	Thickness+2mm	IR 192	ASTM 1B	300MM	1.5-3.5	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****





Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job - No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4569249-000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH - 02536- 01*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00010	1	Absperrschieber mit Handrad Gate valve with handwheel	2"	Cl.600 RF	ASTM A 351 CF8C	Valve Ident - No.: "S 655" LPI 10-S655-W6352

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 150 bar Wasser / water (60 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 110 bar Wasser / water (60 sec)*
Rückdichtung / backseat = 110 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (60 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG
Werksachverständiger:
Manufacturer's authorized inspector: *Water Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*

1

2

3

4



Datum / Date	25.02.2005
--------------	------------

Seite / Page
1 / 1



Lurgi Job - No.: 69690-10
Lurgi OGC PO- No.: 4569249 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

01.03.2005

○

○

○

○

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	CERTIFICADO DE MATERIALES s/ MILL CERTIFICATE Acc. To	Nº/Nr.: W6352
		DATE: 20/12/04
		SHEET:

Cliente/Cient.: KLAUS UNION Armaturen International Bremer Str. 53 D-21244 Buchholz	Pedido Nº Purchase Order: HH-02536-01	Cantidad: Quantity: 3
	Anagrama del Fabricante / sello del Inspector: Manufacturer's Logo / Inspector stamp:	
		

TRATAMIENTO TERMICO HEAT TREATMENT	Normalizado: ☐	Normalizado+Revenido: ☐	Templado+Revenido: ☐	Solubilización: ☒
	Normalized:	Normalized+Tempered	Quenched+Tempered:	Solution:

H.T. CONDICION CONDITION T.T.	SOLUTION 1050 °C	MODO DE FUSION: INDUCTION MELTING TYPE OF MELTING:
--	------------------	---

DENOMINACION DE LA PIEZA: CASTING DENOMINATION:	Gate Body	2" - 600 Lbs	Heat No.:	6952
	Gate Bonnet	2" - 600 Lbs	Heat No.:	6952
	Gate Wedge	2" - 600 Lbs	Heat No.:	6952

CALIDAD DE ACERO: STEEL QUALITY:	ASTM A 351 CF8C	CONDICIONES DE ENTREGA: TERMS OF DELIVERY:	NACE MR 01-75:00
---	-----------------	---	------------------


ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS											Nº de Piezas Ner. Pieces	Peso kgs. Weight
COLADA HEAT No.	C	Mn	Si	P	S	Cr	Mo	Ni	Cu	V		
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			
6952	0.062	0.79	1.25	0.024	0.026	18.54	9.44	0.018	0.62		3	

PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370										
COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	L. Elástico Yield Point N/mm ²	Resistencia Tensile Str. N/mm ²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20 °C		
Solicitado Requirements	Lo = 4D	12.5	205	485	.30		232	60		
6952	Lo = 4D	12.5	242	500	39	62	196	65	67	66
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gamma-graphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los **certificados 3.1.B** correspondientes s/ **EN 10204**, que obran en nuestro poder, emitidos por los suministradores homologados

We hereby certify that the material described above, has been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding **3.1.B. certificates** acc. to **EN 10204**, which are field in our factory, emitted by our homologated suppliers.

Quality Control Department





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 10-S655-W6352

Work Order: W6352-25/12

Customer: KLAUS UNION

Valve Type: Gate Valve 600Lb 2"

Heat No.: 6952

Drawing: 1. 600Lb RF

Part: Flange end

Item: 10

P. O. No.: HH-02536-01

Quantity: 1

Serials No.: W6352

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 28, 2005

Date January 28, 2005

Date

Date



Postfach 10 13 49
D - 44713 Bochum
Blumenfeldstr. 18
D - 44795 Bochum

Telefon (0234) 4595 - 0
Telefax (0234) 43 23 87

Abnahmeprüfzeugnis DIN EN 10204 - 3.1B

Inspection certificate

Besteller: *Lurgi Öl Gas Chemie GmbH, D-60295 Frankfurt*
Customer:

Bestell-Nr.: *Lurgi Job – No.: 69690-10*
Order no.: *Lurgi OGC PO.-No.: 4569249--000/1.69690/136*

Project Name : *2nd Zagros Methanol Plant - Iran*

Auftrag-Nr.: *HH – 02536 - 01*
Job no.:

Lieferumfang / range:

Pos	Stck. pcs.	Gegenstand object	DN	PN	Werkstoff material	Bemerkung comment
00020	1	Absperrschieber mit Getriebe Gate valve Gear operated	10"	Cl 900 BW 273,0 x 12,7	ASTM A 351 CF8C	Valve Ident – No.: "S 657G" LPI 20-S657G-W6353 RE W6353

Auslegung + Prüfung nach *API 600 / API 598 / Nace MR 0175*
Design and tests acc. to

Sicht- und Funktionsprüfung: *o.k.*
visual and functional test:

Festigkeits-/Dichtheitsprüfung: *Festigkeit / shell test = 225 bar Wasser / water (120 sec)*
strength-/tightness-test: *Dichtheit Sitz / seat = 165 bar Wasser / water (120 sec)*
Rückdichtung / backseat = 165 bar Wasser / water (60 sec)
Dichtheit Sitz / seat = 4-7 bar Luft / air (120 sec)

Prüfungsergebnis: *ohne Beanstandung !*
result: *no complaint !*

Bochum, den 25.02.2005 - WG **KLAUS UNION** GmbH & Co. KG
Werksachverständiger:
Manufacturer's authorized inspector: *Walter Glass*

Anlage: *Dokumentation gemäß Material-Dokumentationsdeckblatt*
enclosure *Documentation acc. to material cover sheet*



Datum / Date	25.02.2005
--------------	------------

Seite / Page 1

Sachbearbeiter
W. Glass

Person in charge

Lurgi Job - No.: 69690-10
Lurgi OGC PO,- No.: 4569249 - 000 / 1.69690 / 136

Project Name: 2nd Zagros Methanol Plant - Iran

Zeugnis-Nr.



SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

**CERTIFICADO DE MATERIALES s/
MILL CERTIFICATE Acc. To**

Nº/Nr.: W6353

DATE: 20/12/04

SHEET:

Cliente/Client.:

KLAUS UNION
Armaturen International
Bremer Str. 53
D-21244 Buchholz

Pedido Nº

Purchase Order: HH-02536-01

Cantidad:

Quantity: 3

Anagrama del Fabricante / sello del Inspector:
Manufacturer's Logo / Inspector stamp:



**TRATAMIENTO TERMICO
HEAT TREATMENT**

Normalizado:



Normalized:

Normalizado+Revenido



Normalized+Tempered

Templado+Revenido:



Quenched+Tempered:

Solubilización:



Solution:

**I.T. CONDICION
CONDITION T.T.**

SOLUTION 1050 °C

MODO DE FUSION:

INDUCTION MELTING

TYPE OF MELTING:

**DENOMINACION DE LA PIEZA:
CASTING DENOMINATION:**

Gate Body

10" - 900 Lbs

Heat No.:

K48058

Gate Bonnet

10" - 900 Lbs

Heat No.:

K48058

Gate Wedge

10" - 900 Lbs

Heat No.:

K48058

**CALIDAD DE ACERO:
STEEL QUALITY:**

ASTM A 351 CF8C

**CONDICIONES DE ENTREGA:
TERMS OF DELIVERY:**

NACE MR 01-75:00

ANÁLISIS QUÍMICO - CHEMICAL ANALYSIS

COLADA HEAT No.	C	Mn	Si	P	S	Cr	Mo	Ni	Cu	V		Nº de Piezas Ner. Pieces	Peso kgs. Weight
Solicitado Requirements (max)	0.08	2.00	1.50	0.040	0.040	18.0- 21.0	9.0- 12.0	0.50	8C- 1.00			3	
K48058	0.059	0.64	1.20	0.021	0.024	18.64	9.53	0.018	0.76				


PROPIEDADES MECANICAS / MECHANICAL PROPERTIES Acc. To ASTM A 370

COLADA HEAT No.	Probeta Test Sample	Diametro (mm) Diameter Ø	L. Elástico Yield Point N/mm²	Resistencia Tensile Str. N/mm²	Alargamiento Elongation %	Estricción Red. of Area %	Dureza Hardness HB	Resiliencia Impact Test (ISO V Prob) J; T 20 °C		
Solicitado Requirements	Lo = 4D	12.5	205	485	.30		232	60		
K48058	Lo = 4D	12.5	253	505	42	65	199	68	60	69
Insp. Visual y C. Dimensional Visual Insp. And Dimens check		Ensayo Magnaflux Magnaflux test		Insp. Por Gammagrafia Gammagraphic Inspection		Ensayo de Presión Pressure Test		Insp. Por Ultrasonidos Ultrasonic Test		
S/ MSS-SP-55		Satisfactory								

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados 3.1.B. correspondientes s/ EN 10204, que obran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that the material described above, has been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding 3.1.B. certificates acc. to EN 10204, which are field in our factory, emitted by our homologated suppliers.

Quality Control Department





SPECIALTY VALVES RESEARCH, S.A.
VALVES MANUFACTURER

LIQUID PENETRANT INSPECTION

Certificate No.: 20-S657G-W6353

Work Order: W6353-25/12

Customer: KLAUS UNION

Valve Type: Gate Valve 900Lb 10"

Heat No.: K48058

Drawing: 1. 900Lb BW

Part: BW end

Item: 20

P. O. No.: HH-02536-01

Quantity: 1

Serials No.: W6353

Surface Conditions: AS RAW

Material: ASTM A351 CF8C

Reference Procedure: E165

Acceptance Standards: ANSI B 16.34

Precleaned by: WATER

Type of penetrant: HP-ST

Rinsed by: HD-ST

Type of developer: HR-ST

Penetr. Time (min.): 5-20

Developer Time (min.): 7-30

Temperature (°C): 15°C

INTERPRETATION OF TEST RESULTS:

	YES	NO	ACCEPT.	NOT ACCEPT.
Linear indications	☐	☒	☒	☐
Group of linear indications	☐	☒	☒	☐
Non linear indications	☐	☒	☒	☐

Sketch of Discontinuities:

RESULTS:

☒ Conforming
☐ Non Conforming

REPAIR OF DISCONTINUITIES MADE BY:

REINSPECTED BY:

☐ Accepted

☐ Rejected

SVR - SPECIALTY VALVES RESEARCH

INSPECTORS

Examination by
Level II SNT-TC-1A
EN 473

Approved by
Level II SNT-TC-1A
EN 473

WITNESS POINT CUSTOMER

☐ YES ☐ NOT ☐ OTHERS

Sign.

Sign.

Sign.

Sign.

Date January 28, 2005

Date January 28, 2005

Date

Date

 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAIN)
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC EXAMINATION REPORT FOR CASTINGS

Procedure:	ASME B 16.34	Report No.:	W6353
------------	--------------	-------------	-------

Page: 1 / 2

Customer : KLAUS UNION	Contract: HH-02536-01
Description : GATE BODY	Extension of Test: BW-ENDS
Drawing : 90OLB 10"	Radiographed at: Shop: ☒ Field: ☐
Material : CF8C Heat Number: K48058	


X Rays KV	Γ RAYS	Isotope : IR 192	Curies: 40	Focal Spot Size: 3x3
Film Type, Brand and Size : KODAK AA400,360x80		IQI: ASTM 1B 16		
Screens Type and Thickness : Pb,0.03/0.10		Material Thickness: Thickness+2mm		
Density : 1.5-4.0	Source Film Distance : 450MM	Exposure Time: 3 min - 30 min		

Evaluation standard for steel castings radiographic examination (See Back)	Acceptance Standard
Sketch of geometric arrangement of radiographs and location markers in attached form	ASME B 16.34

Identification	Interval	Viewing	Evaluation	Observed Defects							
				Porosity	Sand	Shrinkage	Cracks	Hot Tears	Others	Superf.	Accepted
R1	1-2		II	/	/	/	/	/	/	I	OK
R2	2-3		II	/	/	CB2	/	/	/	II	OK
R3	3-4		II	/	/	/	/	/	/	I	OK
R4	4-1		II	/	/	/	/	/	/	I	OK
R5	5-6		II	/	/	/	/	/	/	I	OK
R6	6-7		II	/	B1	/	/	/	/	I	OK
R7	7-8		II	/	/	/	/	/	/	I	OK
R8	8-5		II	/	/	/	/	/	/	I	OK
R9	9-10		II	/	/	/	/	/	/	I	OK
R10	10-11		II	A2	/	/	/	/	/	II	OK
R11	11-12		II	A1	/	/	/	/	/	I	OK
R12	12-9		II	/	B1	/	/	/	/	I	OK
R13	13		II	/	/	CA1	/	/	/	I	OK
R14	14		II	/	/	/	/	/	/	I	OK
R15	15		II	/	/	CA2	/	/	/	II	OK
R16	16		II	/	/	/	/	/	/	I	OK
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****	*****

Certificamos que el material descrito aquí ha sido ensayado y cumple con los requisitos solicitados por el cliente. Los resultados arriba indicados son fiel reflejo de los certificados correspondientes, que abran en nuestro poder, emitidos por los suministradores homologados.

We hereby certify that material described above, have been tested and complies to the material requirements of the purchase order. The results above indicated are exact transcription from the corresponding certificates, which are field in our factory, emitted by homologated suppliers.



 SPECIALTY VALVES RESEARCH, S.A. VALVES MANUFACTURER	ADDRESS:	ARETXALDE, 150 48196 LEZAMA -BIZKAIA- (SPAII
	PHONE:	+ (34) 94. 455. 51. 51
	FAX:	+ (34) 94. 455. 51. 50
	WEBB:	www.svrvalves.com
	E-mail:	webmaster@svrvalves.com

RADIOGRAPHIC MAP

Page: 2 / 2

Procedure:	ASME B 16.34		
Customer:	KLAUS UNION	Heat:	K48058
Contract:	HH-02536-01	Part No.	W6353
Drawing:	900LB 10"	Descriptions:	GATE BODY

Radiografy No.	Type and Size of Film	Thickness	Source	I.Q.I.	Focus-Film Distance	Density	Back Shielding
R1 - R16	KODAK AA400	50-60	IR 192	ASTM 1B 16	450MM	1.5-4.0	Pb
*****	*****	*****	*****	*****	*****	*****	*****
*****	*****	*****	*****	*****	*****	*****	*****

